

DIPHOSPHINES, PREPARATION AND USES THEREOF

The present invention relates to novel diphosphines especially in their optically active form, and also to  
5 the process for obtaining them.

The invention is also directed toward their uses as bidentate ligands in the synthesis of transition metal-based catalysts for asymmetric catalysis.

10

The invention is also directed toward their uses as intermediate products in the preparation of ligands in insoluble form. More particularly, the invention lies in an optically active polymer in which one of the  
15 polymer units consists of a chiral diphosphine.

The invention is also directed toward the use of said polymer as a ligand in the preparation of metal complexes for asymmetric catalysis.

20 The production of pure optically active compounds is a problem that arises in many technical fields, for instance pharmacy, agrochemistry, the food industry (food additives and flavorings) and also in the fragrance industry.

25

This problem is expected to become increasingly important since it has been found more and more that, in a given application, only one of the stereoisomers has the desired property.

30

Asymmetric catalysis has undergone considerable expansion in recent years. It has the advantage of leading directly to the preparation of optically pure or optically enriched isomers by asymmetric induction  
35 without it being necessary to perform resolution of racemic mixtures.

2,2'-Bis(diphenylphosphino)-1,1'-binaphthyl (BINAP) is an example of a diphosphorus ligand commonly used for the preparation of metal complexes for the asymmetric catalysis of hydrogenation, carbonylation, hydrosilylation and C-C bond forming reactions (such as allylic substitutions or Grignard cross-couplings) or even asymmetric isomerization reactions of allylamines.

The complexes used are derivatives of palladium, ruthenium, rhodium and iridium salts.


The development of novel chiral ligands is desirable for several reasons.

Ligands that are capable of improving the enantioselectivity of reactions are sought.

There is also a need for ligands that are industrially readily accessible.

Thus, document WO 00/49028 describes a diphosphine that is a BINAP derivative, the two naphthyl groups of which bear a substitution in position 6 and 6'. The agent more specifically concerned is 6,6'-diaminomethylBINAP.

However, the preparation of this phosphine is not readily achievable industrially, since it includes numerous steps:



In the pursuit of its research, the Applicant has found that it is possible to prepare diphosphines that may be prepared much more readily on an industrial scale since they are derived from a commercial product, namely 2,2'-bis(diphenylphosphino)-1,1'-binaphthyl or BINAP.


A first subject of the invention is diphosphines in which the naphthyl groups are substituted in the 5,5' position.

Another subject of the invention is intermediate products that are diphosphines in dioxide form containing substituents in the 5,5' position.

The invention is directed not only toward the racemic mixture but also toward the optically active forms of said diphosphines.

Other subjects of the invention are the processes for preparing said disphosphines, and the uses thereof in asymmetric catalysis.

- 5 The present invention thus provides a diphosphine that may be used as ligands in chiral catalysts, and corresponding to formula (I):




10

in said formula:


- $R_1$  and  $R_2$ , which may be identical or different, represent a hydrogen atom or a substituent,
  - $Ar_1$  and  $Ar_2$  independently represent an alkyl, alkenyl, cycloalkyl, aryl or arylalkyl group,
  - $X_1$  and  $X_2$ , which may be identical or different, represent:
    - . a group R, alkyl, alkenyl, alkynyl, cycloalkyl, aryl or arylalkyl,
    - . an alkyl group substituted with one or more halogen atoms, preferably fluorine, or with nitro or amino groups,
    - . a halogen atom chosen from bromine, chlorine and iodine,
    - . an -OH group,
    - . a group -O- $R_a$ ,
    - . a group -O-CO $R_a$ ,
    - . a group -S- $R_a$ ,
- 15  
20  
25

- . a -CN group,
  - . a group derived from the nitrile group such as:
    - . a -CH<sub>2</sub>-NH<sub>2</sub> group,
    - . a -COOH group,
  - 5 . a group derived from the carboxylic group such as:
    - . a group -COOR<sub>a</sub>,
    - . a -CH<sub>2</sub>OH group,
    - . a group -CO-NH-R<sub>b</sub>,
  - 10 . a group derived from the aminomethyl group such as:
    - . a group -CH<sub>2</sub>-NH-CO-R<sub>b</sub>,
    - . a group -CH<sub>2</sub>-NH-CO-NH-R<sub>b</sub>,
    - . a group -CH<sub>2</sub>-N=CH-R<sub>a</sub>,
  - 15 . a -CH<sub>2</sub>-N=C=O group,
  - . a -CH<sub>2</sub>-NH<sub>4</sub><sup>+</sup> group,
  - . a group comprising a nitrogen atom such as:
    - . a group -NHR<sub>a</sub>,
    - . a group -N(R<sub>a</sub>)<sub>2</sub>,
  - 20 . a group -N=CH-R<sub>a</sub>,
  - . an -NH-NH<sub>2</sub> group,
  - . an -N=N<sup>+</sup>=N<sup>-</sup> group,
  - . an -N=C=O group,
  - . a magnesium or lithium atom,
  - 25 in the various formulae, R<sub>a</sub> represents an alkyl, cycloalkyl, arylalkyl or phenyl group and R<sub>b</sub> has the meaning given for R<sub>a</sub> and also represents a naphthyl group.
- 30 The present invention is also directed toward the intermediate products, i.e. the diphosphine in dioxide form, in racemic form or in chiral form, and which corresponds to the following formula:



in said formula (II),  $R_1$ ,  $R_2$ ,  $Ar_1$ ,  $Ar_2$ ,  $X_1$  and  $X_2$  have the meaning given for formula (I).

5 Among the diphosphines corresponding to the general formula (I), one particularly advantageous group of diphosphines is that consisting of the diphosphines corresponding to formula (I'), which may be used as intermediate products for the preparation of insoluble  
 10 polymers as constituents of one of the polymer units:



in said formula:

- 15
- $R_1$  and  $R_2$ , which may be identical or different, represent a hydrogen atom or a substituent,
  - $Ar_1$  and  $Ar_2$  independently represent an alkyl, alkenyl, cycloalkyl, aryl or arylalkyl group,

- $X_1$  and  $X_2$ , which are identical, represent:
  - . an -OH group,
  - . a -CH<sub>2</sub>OH group,
  - . a -CH<sub>2</sub>-NH<sub>2</sub>,
  - 5 . a -COOH group,
  - . a group -COOR<sub>a</sub> in which R<sub>a</sub> represents an alkyl, cycloalkyl, arylalkyl or phenyl group,
  - . an -N=C=O group,
  - . a -CH<sub>2</sub>-N=C=O group.

10

The characteristic of the diphosphines of formula (I') is that they bear two functional groups capable of reacting with one or more polymerizable monomers leading to a polymer which, when it is obtained from a  
 15 chiral diphosphine, is optically active and is thus able to be used as a ligand in metal complexes used in asymmetric catalysis.

The definition of certain terms used in the present  
 20 text is recalled hereinbelow.

The term "chiral" refers to a molecular species that is not superposable on its mirror image.

25 A compound is racemic if it is the equimolar mixture of its two enantiomeric forms. The term "enantiomers" denotes molecular species that are mirror images of each other and that are not superposable.

30 A compound is optically active if it is capable of rotating the plane of polarization of a transmitted beam of plane polarized light. An optically active compound is necessarily chiral.

35 In the context of the invention, the term "alkyl" means a linear or branched hydrocarbon-based chain containing

from 1 to 15 carbon atoms and preferably 1 or 2 to 10 carbon atoms.

Examples of preferred alkyl groups are especially  
5 methyl, ethyl, propyl, isopropyl, butyl, isobutyl and t-butyl.

The term "alkenyl" means a linear or branched hydrocarbon-based group containing from 2 to 15 carbon  
10 atoms, comprising one or more double bonds and preferably one or two double bonds.

The term "alkynyl" means a linear or branched hydrocarbon-based group containing from 2 to 15 carbon  
15 atoms, comprising one or more triple bonds and preferably one triple bond.

The term "cycloalkyl" means a cyclic hydrocarbon-based group, which is monocyclic comprising from 3 to  
20 8 carbon atoms, preferably a cyclopentyl or cyclohexyl group, or polycyclic (bicyclic or tricyclic) comprising from 4 to 18 carbon atoms, especially adamantyl or norbornyl.

25 The term "aryl" means a monocyclic or polycyclic, preferably monocyclic or bicyclic, aromatic group comprising from 6 to 20 carbon atoms, preferably phenyl or naphthyl. When the group is polycyclic, i.e. when it comprises more than one cyclic nucleus, the cyclic  
30 nuclei may be fused in pairs or attached in pairs via  $\sigma$  bonds.

Examples of (C<sub>6</sub>-C<sub>18</sub>)aryl groups are especially phenyl, naphthyl, anthryl and phenanthryl.

35

The term "arylalkyl" means a linear or branched



hydrocarbon-based group bearing a monocyclic aromatic ring and comprising from 7 to 12 carbon atoms, preferably benzyl.

- 5 In formula (I), (I') or (II), the carbocyclic groups  $Ar_1$  and  $Ar_2$  may bear substituents which are such that they do not interfere with the complexation of the ligand to the metal during the preparation of the catalyst.
- 10 Examples of substituents are alkyl, alkoxy, thioalkoxy, alkoxyalkyl, thioalkoxyalkyl, polyoxyalkylene,  $-SO_3H$ ,  $-SO_3M$  in which M is an ammonium or metal cation,  $-PO_3H_2$ ,  $-PO_3HM$  or  $-PO_3M_2$  groups in which M is as defined above.
- 15 Preferably, M is an alkali metal cation such as Na, Li or K.

It is desirable for the substituents not to interfere with the reactions performed in the preparation of the compounds (I) and (I') starting with the precursors from which they are derived. However, protection and deprotection steps may be envisioned, where appropriate. A person skilled in the art may refer to the following publication *Protective Groups in Organic*  
 20 *Synthesis*, Greene T.W. and Wuts P.G.M., published by John Wiley and Sons, 1991, to perform the protection of particular organic functions.

In the alkyl, alkoxy, thioalkoxy, alkoxyalkyl and thioalkoxyalkyl groups, the alkyl portions are linear or  
 30 branched saturated hydrocarbon-based groups comprising especially up to 25 carbon atoms, for example from 1 to 12 carbon atoms and better still from 1 to 6 carbon atoms.

35

Examples of alkyl groups are methyl, ethyl, propyl,

isopropyl, butyl, isobutyl, t-butyl, pentyl, isopentyl, neopentyl, 2-methylbutyl, 1-ethylpropyl, hexyl, isohexyl, neohexyl, 1-methylpentyl, 3-methylpentyl, 1,1-dimethylbutyl, 1,3-dimethylbutyl, 2-ethylbutyl, 5 1-methyl-1-ethylpropyl, heptyl, 1-methylhexyl, 1-propylbutyl, 4,4-dimethylpentyl, octyl, 1-methylheptyl, 2-ethylhexyl, 5,5-dimethylhexyl, nonyl, decyl, 1-methylnonyl, 3,7-dimethyloctyl and 7,7-dimethyloctyl groups.

10

Preferably, the substituents are alkyl or alkoxy groups preferably containing from 1 to 6 carbon atoms.

In accordance with the present invention, the preferred 15 ligands and the intermediates thereof correspond, respectively, to formula (I), (I') or (II) in which Ar<sub>1</sub> and Ar<sub>2</sub> independently represent a (C<sub>1</sub>-C<sub>6</sub>)alkyl group; a phenyl group optionally substituted with one or more (C<sub>1</sub>-C<sub>6</sub>)alkyl or (C<sub>1</sub>-C<sub>6</sub>)alkoxy groups; or a (C<sub>4</sub>-C<sub>8</sub>)cyclo- 20 alkyl group optionally substituted with one or more (C<sub>1</sub>-C<sub>6</sub>)alkyl groups.

Among the preferred compounds of formula (I), (I') or (II) are those for which Ar<sub>1</sub> and Ar<sub>2</sub> are, independently, 25 a (C<sub>1</sub>-C<sub>4</sub>)alkyl group; a phenyl group optionally substituted with methyl or tert-butyl; or a (C<sub>5</sub>-C<sub>6</sub>)cycloalkyl group optionally substituted with methyl or tert-butyl.

30 The compounds of formula (I), (I') or (II) in which Ar<sub>1</sub> and Ar<sub>2</sub> are identical and preferably represent a phenyl group are most particularly preferred.

The carbocyclic groups Ar<sub>1</sub> and Ar<sub>2</sub> may bear substituents 35 which are such that they do not interfere with the reactions used in the process of the invention. These

substituents are inert under the conditions used in the halogenation (step i), cyanation (step ii) and reduction (steps iii and iv) reactions. Thus, the invention does not exclude the presence of substituents other  
 5 than  $R_1$  and  $R_2$ .

The naphthyl groups may also bear a substituent represented by  $R_1$  or  $R_2$ , which may be of the same nature as those that have just been mentioned.  
 10

Preferably, the substituents are alkyl or alkoxy groups preferably containing from 1 to 6 carbon atoms.

In formulae (I), (I') and (II),  $R_1$  and  $R_2$  preferably  
 15 represent a hydrogen atom or one or more groups chosen from  $(C_1-C_4)$ alkyl and  $(C_1-C_4)$ alkoxy.

The preferred compounds (I), (I') and (II) do not bear a substituent, which means that  $R_1$  and  $R_2$  represent a  
 20 hydrogen atom.


As regards the preferred groups  $X_1$  and  $X_2$ ,  $R_a$  represents an alkyl group containing from 1 to 4 carbon atoms, a cyclohexyl group, a phenyl group and a benzyl group,  
 25 and  $R_b$  has the meaning given for  $R_a$  and also represents a naphthyl group.

The preferred functional groups located in position 5 and 5' in the compounds of formulae (I), (I') and  
 30 (II) are the following:

- . a halogen atom, preferably a bromine or chlorine atom,
- . an alkyl group substituted with one or more fluorine atoms,
- 35 . a -CN group,
- . a  $-CH_2-NH_2$  group,

a -COOH group.

Among the compounds of formula (I) that are especially distinguished are the compounds having the following  
5 formula:




in said formula:

- X represents a chlorine, bromine or iodine atom,
- 10 - R<sub>1</sub>, R<sub>2</sub>, Ar<sub>1</sub> and Ar<sub>2</sub> have the meaning given above.

A first subject of the invention lies in a process for preparing the diphosphine of formula (Ia<sub>1</sub>), characterized in that it comprises the following steps:

15

- i) performing the halogenation in the 5,5' position of a compound of formula (III):




20

in said formula:

- R<sub>1</sub>, R<sub>2</sub>, Ar<sub>1</sub> and Ar<sub>2</sub> have the meaning given above,


using a halogen and in the presence of iron, so as to obtain the corresponding dihalo compound of formula:



in said formula:


- 5     - X represents a chlorine, bromine or iodine atom,  
        - R<sub>1</sub>, R<sub>2</sub>, Ar<sub>1</sub> and Ar<sub>2</sub> have the meaning given above;

ii) performing the reduction of the diphosphine in  
 dioxide and dihalo form in position 5,5' of formula  
 10 (IIa<sub>1</sub>), into the diphosphine of formula (Ia<sub>1</sub>):



in said formula:

- X represents a chlorine, bromine or iodine atom,  
        - R<sub>1</sub>, R<sub>2</sub>, Ar<sub>1</sub> and Ar<sub>2</sub> have the meaning given above.
- 15 The diphosphine in dioxide form of formula (III) is known. It may be obtained by oxidation of the diphosphine of formula (IV):



in said formula:

-  $R_1$ ,  $R_2$ ,  $Ar_1$  and  $Ar_2$  have the meaning given above.

5 The diphosphine in oxide form of formula (III) is obtained by oxidation using an agent for oxidizing the diphosphine of formula (IV).

10 Although any type of oxidizing agent may be used, a chemical oxidizing agent, for example potassium permanganate or alternatively molecular oxygen or a gas containing it, use is preferably made of hydrogen peroxide, preferably in the form of an aqueous solution.

15 The concentration of the hydrogen peroxide solution is advantageously between 10% and 35% by weight.

20 The amount of oxidizing agent used may vary widely from the stoichiometric amount up to a 100% excess relative to the stoichiometry.

25 An organic solvent that dissolves the diphosphine is used. The solvent may be chosen from aliphatic, cycloaliphatic and aromatic hydrocarbons, which may or may not be chlorinated. Examples that may be mentioned include dichloromethane, chloroform, carbon tetrachloride and 1,2-dichloroethane.

The concentration of diphosphine in the reaction

solvent is preferably between 0.1 and 50 g/l.

The diphosphine, generally dissolved in an adequate solvent, is thus placed in contact with the oxidizing agent.

The reaction is advantageously performed at room temperature, usually between -5°C and 25°C.

The reaction time is generally between 30 minutes and 6 hours.

The diphosphine is recovered in dioxide form in the organic phase.

The aqueous and organic phases are separated.

A standard work-up of the phases is performed.

Thus, the organic phase is washed with sodium bisulfite, which removes from the aqueous phase the unreacted excess oxidizing agent (peroxide).

A common drying operation is preferably performed, over a drying agent, for example sodium sulfate or magnesium sulfate.

A diphosphine in dioxide form corresponding to formula (III) and denoted in the text hereinbelow as "diphosphine (PO)" is obtained.

In accordance with the present invention, the halogenation reaction of the naphthyl nucleus is performed, which is an electrophilic reaction performed via the action of a halogen, chlorine, bromine or iodine, on the diphosphine in dioxide form and in the presence of

a catalyst.

This reaction may be performed in the presence of an iron-based catalyst. Iron turnings or filings are  
5 preferably used.

The amount of iron used is such that the ratio between the number of moles of iron and the number of moles of compound of formula (III) ranges between 15 and 30 and  
10 more particularly at about 20.

According to one preferred embodiment of the invention, the halogenation takes place in an inert aprotic solvent.

15 Said solvent should have a boiling point of greater than 60°C. Chlorinated or brominated halogenated hydrocarbons are most particularly used, preferably chloroform, carbon tetrachloride or 1,2-dichloroethane.

20 A preferred solvent that may be mentioned is 1,2-dichloroethane.

Preferably, the molar ratio of the halogenating agent  
25 to the diphosphine (PO) ranges between 15 and 30 and preferably at about 20.

When the process is performed in solution, the concentration of the reagents may vary very widely between  
30 0.01 and 10 mol/l, for example between 0.05 and 1 mol/l.

The halogenation reaction, preferably the bromination, is performed between 20°C and 100°C and advantageously  
35 in the absence of light so as to avoid spurious radical reactions.



A dihalo diphosphine (PO) corresponding to formula (IIa<sub>1</sub>) is thus obtained.

It is recovered in a conventional manner: neutralization of the excess bromine with sodium disulfite, treatment with a base (sodium carbonate or sodium hydrogen carbonate), separation of the aqueous and organic phases and then recovery of the dihalo diphosphine (PO) from the organic solution, which is dried followed by removal of the organic solvent.


In step (ii), the phosphorus atom in oxidized form (PO) is reduced to give the diphosphine of formula (Ia<sub>1</sub>).

In a following step, reduction of the diphosphine in dioxide form is performed.

This step consists in subjecting said diphosphine to a reduction performed using a hydrogenosilane.

20

Said hydrogenosilane may be represented by the following formula:



25

in said formula:

- R<sub>α</sub>, R<sub>β</sub> and R<sub>δ</sub>, which may be identical or different, represent a hydrogen atom, an alkyl group containing from 1 to 6 carbon atoms, a phenyl group or a chlorine atom,
- at most two of the groups R<sub>α</sub>, R<sub>β</sub> and R<sub>δ</sub> represent a hydrogen atom.

The preferred reducing agents correspond to formula (F<sub>a</sub>) in which R<sub>α</sub>, R<sub>β</sub> and R<sub>δ</sub> represent a hydrogen atom, a methyl group, a phenyl group or a chlorine atom.

Examples of reducing agents that may be mentioned more particularly include:

- $\text{AlH}_3$ ,
- 5    -  $\text{PhSiH}_3$ ,
- $\text{HSiCl}_3$ ,
- $(\text{CH}_2)_2\text{HSiCl}$ ,
- $\text{CH}_3(\text{HSiCl})$
- PMHS or polymethylhydrosiloxane.

10

The invention does not exclude any other type of organosilicon compound comprising an SiH group.

The amount of reducing agent is usually a large  
15 stoichiometric excess.

Thus, the ratio between the number of moles of reducing agent and the number of moles of diphosphine (PO) ranges between 10 and 70.

20

Among the abovementioned reducing agents, a mixture of  $\text{PhSiH}_3$  (or PMHS) and of  $\text{HSiCl}_3$  is used.

In this case, the amount of  $\text{PhSiH}_3$  is such that the  
25 ratio between the number of moles of  $\text{PhSiH}_3$  and of moles of diphosphine (PO) ranges between 50 and 70.

As regards the amount of  $\text{HSiCl}_3$ , the ratio between the number of moles of  $\text{HSiCl}_3$  and the number of moles of  
30 diphosphine (PO) ranges between 10 and 40.

The reduction reaction is performed at a temperature advantageously chosen between  $80^\circ\text{C}$  and  $130^\circ\text{C}$ .


35 At the end of reaction, the medium is cooled to room temperature and the product is recovered in solid form

after evaporation.

The product may be washed one or more times using an organic solvent, preferably a halogenated or non-halogenated aliphatic, cycloaliphatic or aromatic hydrocarbon. Preferred solvents that may be mentioned include pentane, hexane and cyclohexane.

A diphosphine corresponding to formula (Ia<sub>1</sub>) is obtained.


The present invention also provides the process for obtaining a diphosphine corresponding to formula (Ia<sub>2</sub>):



in which R<sub>1</sub>, R<sub>2</sub>, Ar<sub>1</sub> and Ar<sub>2</sub> are as defined above.


The process of the invention for obtaining the diphosphine of formula (Ia<sub>2</sub>) more specifically comprises the following steps:

i) performing the substitution of the two halogen atoms, preferably bromine atoms, with cyano groups by reacting the diphosphine in dioxide and dihalo form in position 5,5' of formula (IIa<sub>1</sub>):



in said formula:

- X, R<sub>1</sub>, R<sub>2</sub>, Ar<sub>1</sub> and Ar<sub>2</sub> have the meaning given above,  
using a suitable nucleophilic reagent so as to obtain  
5 the corresponding dicyano compound (IIa<sub>2</sub>):




in said formula:

- R<sub>1</sub>, R<sub>2</sub>, Ar<sub>1</sub> and Ar<sub>2</sub> have the meaning given above,

10

- ii) performing the reduction of the diphosphine in  
dioxide and dicyano form in position 5,5' of formula  
(IIa<sub>2</sub>) into the diphosphine of formula (Ia<sub>2</sub>):



in said formula:

- R<sub>1</sub>, R<sub>2</sub>, Ar<sub>1</sub> and Ar<sub>2</sub> have the meaning given above.

5

Starting with a diphosphine in dioxide and dihalo form of formula (IIa<sub>1</sub>), the next step is a cyanation reaction, which is a nucleophilic substitution. The two halogen atoms borne by the naphthyl nuclei are replaced with cyano groups via the action of a suitable nucleophilic agent.

To perform this substitution, a person skilled in the art may use any of the methods known in the art.

15

According to one preferred embodiment of the invention, the nucleophilic agent used is copper(I) or (II) cyanide.

20 The molar ratio of the copper cyanide to the compound of formula (IIa<sub>1</sub>) is preferably greater than 2, advantageously between 2 and 4 and preferably between 2 and 3.

25 The reaction is preferably performed in a solvent. Examples of solvents that may be mentioned include amides such as dimethylformamide, N-methyl-2-pyrrolid-

inone and hexamethylphosphorylamide. Dimethylformamide is markedly preferred. Pyridine is also a suitable solvent.

- 5 The reaction temperature is advantageously maintained between 50°C and 200°C and preferably between 100°C and 190°C.

The concentration of reagents in the reaction medium  
10 generally varies between 0.1 and 10 mol/l, for example between 2 and 7 mol/l.

The isolation of the nitrile involves decomposition of the intermediate complex formed and trapping of the  
15 excess cyanide.

The hydrolysis of the intermediate complex may be performed either via the action of hydrated iron chloride or via the action of aqueous ethylenediamine.

20

In the first case, the reaction medium is poured into an aqueous 50-80% (g/ml) iron chloride solution containing concentrated hydrochloric acid. The resulting solution is heated to 40-80°C until the complex has  
25 completely decomposed. The medium is then decanted and extracted in a conventional manner.

In the second case, the reaction medium is poured into an aqueous ethylenediamine solution (ethylenediamine/-  
30 water: 1/5-1/1 (v/v), for example 1/3) and the mixture is then stirred vigorously. The medium is then decanted and extracted in a manner known per se.

A person skilled in the art may take inspiration from  
35 the studies of L. Friedman et al. published in J.O.C. 1961, 26, 1522, to isolate the nitrile.


Starting with the dicyano diphosphine (PO) of formula (IIa<sub>2</sub>), the compound of formula (Ia<sub>2</sub>) is obtained by reduction of the diphosphine in dioxide form as described above.

5

The present invention moreover provides a process for converting the compounds of formula (Ia<sub>2</sub>) (which contain two cyano functions) into the corresponding diamino-methyl compounds.

10

Thus, according to another of its aspects, the invention relates to a process comprising, in addition to the steps (i) and (ii) defined above for the preparation of the diphosphine of formula (Ia<sub>2</sub>), an additional step of reduction of the nitrile function of the compound of formula (Ia<sub>2</sub>) via the action of a reducing agent, so as to obtain a compound of formula (Ia<sub>3</sub>):

20

in said formula:

- R<sub>1</sub>, R<sub>2</sub>, Ar<sub>1</sub> and Ar<sub>2</sub> have the meaning given above.

In a following step, the reduction of the cyano group is performed.

25

A suitable reducing agent is lithium aluminum hydride (LiAlH<sub>4</sub>).

The invention is not intended to be limited to the use of this particular reducing agent.

The reaction is preferably performed in a solvent or a  
5 mixture of solvents.

When the reducing agent is  $\text{LiAlH}_4$ , the solvent advantageously comprises one or more aromatic hydrocarbons (such as benzene, toluene and xylene) as a  
10 mixture with one or more ethers.

Ethers that may be mentioned include  $\text{C}_1\text{-C}_6$  alkyl ethers (diethyl ether and diisopropyl ether), cyclic ethers (dioxane or tetrahydrofuran), dimethoxyethane and  
15 diethylene glycol dimethyl ether.

Cyclic ethers such as tetrahydrofuran are preferred.

When the reducing agent is  $\text{LiAlH}_4$ , a mixture of toluene  
20 and tetrahydrofuran in proportions ranging between 70-50/30-50: toluene/tetrahydrofuran (for example 60/40: toluene/THF) (v/v) will more preferably be selected.

The reduction may be performed at a temperature of  
25 between  $20^\circ\text{C}$  and  $100^\circ\text{C}$  and preferably between  $40^\circ\text{C}$  and  $80^\circ\text{C}$ .

A large excess of the reducing agent is usually used. Thus, the molar ratio of the reducing agent to the  
30 compound of formula (Ia<sub>2</sub>) generally ranges between 1 and 30, for example between 2 and 20 and especially between 5 and 18.

The concentration of reagents in the medium is  
35 variable. It may be maintained between 0.005 and 1 mol/l.



A compound of formula (Ia<sub>3</sub>) is obtained, which may be recovered in a conventional manner, especially by treatment with a base (sodium hydroxide) to remove the  
5 aluminates, followed by filtration, drying and evaporation.

The compounds of formula (Ia<sub>3</sub>) obtained according to the process of the invention are novel and form another  
10 subject of the invention.


Among these compounds, the ones that are preferred are those for which Ar<sub>1</sub> and Ar<sub>2</sub> are chosen from a (C<sub>1</sub>-C<sub>4</sub>)-alkyl group from phenyl optionally substituted with  
15 methyl or tert-butyl; and (C<sub>5</sub>-C<sub>6</sub>)cycloalkyl optionally substituted with methyl or tert-butyl.

The compounds of formula (Ia<sub>3</sub>) in which Ar<sub>1</sub> and Ar<sub>2</sub> are identical and represent a phenyl group are more  
20 preferably chosen.

As a variant, it is possible to convert the two cyano functions of the compounds of formula (Ia<sub>2</sub>) into carboxylic acid, imine, hydroxymethyl or amide  
25 functions.

The products resulting from these conversions are ligands that may also be used in asymmetric catalysis.

30 As a variant, the invention provides a process comprising, in addition to steps (i) and (ii) defined above, the step consisting in treating, in acidic medium or in basic medium, the compound of formula (Ia<sub>2</sub>) so as to obtain the corresponding carboxylic acid of formula  
35 (Ia<sub>4</sub>):



in said formula:

- R<sub>1</sub>, R<sub>2</sub>, Ar<sub>1</sub> and Ar<sub>2</sub> have the meaning given above.

5

The conversion of a nitrile function into a carboxylic acid function is described in the standard texts of organic chemistry. Thus, a person skilled in the art can readily determine the appropriate reaction conditions.

10

One simple way of proceeding consists in using aqueous sodium hydroxide as hydrolysis agent.

15 As a variant, it is possible to convert the two carboxylic functions of the compounds of formula (Ia<sub>4</sub>) into ester, hydroxymethyl or amide functions.

A diphosphine of formula (Ia<sub>5</sub>) that corresponds to formula (I) or (I') in which X<sub>1</sub> and X<sub>2</sub> represent a group -COOR<sub>a</sub> is obtained by direct esterification of the compound of formula (Ia<sub>4</sub>), performed conventionally in basic medium.

20

25 A diphosphine of formula (Ia<sub>6</sub>) that corresponds to formula (I) or (I') in which X<sub>1</sub> and X<sub>2</sub> represent a -CH<sub>2</sub>OH group is obtained by reduction of the compound of formula (Ia<sub>4</sub>) using, for example, LiAlH<sub>4</sub> or NaH

[Gaylord, N.G. *Reduction with complex metals hydride*; Wiley: NY, 1956, p. 322].

A diphosphine of formula (Ia<sub>7</sub>) that corresponds to  
5 formula (I) or (I') in which X<sub>1</sub> and X<sub>2</sub> represent a group  
-CO-NH-R<sub>b</sub> is obtained by reaction of the compound of  
formula (Ia<sub>4</sub>) with an amine R<sub>b</sub>-NH<sub>2</sub> in the presence of a  
coupling agent, for instance DCC (dicyclohexyl carbam-  
ate) (Klausner Y.S., Bodansky M., *Synthesis*, 1972,  
10 453).

As a variant, it is possible to convert the two amino-  
methyl functions of the compounds of formula (Ia<sub>3</sub>) into  
amide or urea functions.

15

A diphosphine of formula (Ia<sub>8</sub>) that corresponds to  
formula (I) or (I') in which X<sub>1</sub> and X<sub>2</sub> represent a group  
-CH<sub>2</sub>-NH-CO-R<sub>b</sub> is obtained by reacting the compound of  
formula (Ia<sub>3</sub>) with an acid R<sub>b</sub>-COOH in the presence of a  
20 coupling agent, for instance DCC (Klausner Y.S.,  
Bodansky M., *Synthesis*, 1972, 453).

A diphosphine of formula (Ia<sub>9</sub>) that corresponds to  
formula (I) or (I') in which X<sub>1</sub> and X<sub>2</sub> represent a group  
25 -CH<sub>2</sub>-NH-CO-NH-R<sub>b</sub> is obtained by reacting the compound of  
formula (Ia<sub>3</sub>) with an isocyanate R<sub>b</sub>-NCO generally in  
solvent medium [Rob Ter Halle, Benoit Colasson,  
Emanuelle Schulz, Michel Spagnol, Marc Lemaire,  
*Tetrahedron Letters*, 2000, (41) 643-646].

30

A diphosphine of formula (Ia<sub>10</sub>) that corresponds to  
formula (I) or (I') in which X<sub>1</sub> and X<sub>2</sub> represent a group  
-CH<sub>2</sub>-N=CH-R<sub>a</sub> is obtained by reacting the compound of  
formula (Ia<sub>3</sub>) with an aldehyde R<sub>a</sub>-CHO (Farrar W.V., *Rec.*  
35 *Chem. Prog.*, 1968, 29, 85).

A diphosphine of formula (Ia<sub>11</sub>) that corresponds to formula (I) or (I') in which X<sub>1</sub> and X<sub>2</sub> represent a -CH<sub>2</sub>-N=C=O group is obtained by reaction of the compound of formula (Ia<sub>3</sub>) with phosgene, performed according to the  
5 teaching of the literature especially by Jerry March, Advanced Organic Chemistry, 5th Edition, John Wiley and Sons, p. 507.

A diphosphine of formula (Ia<sub>12</sub>) that corresponds to  
10 formula (I) or (I') in which X<sub>1</sub> and X<sub>2</sub> represent a -CH<sub>2</sub>-NH<sub>4</sub><sup>+</sup> group is obtained by placing the compound of formula (Ia<sub>3</sub>) in contact with an acid, preferably hydrobromic acid, at room temperature, in a suitable solvent capable of dissolving the compound of formula (Ia<sub>3</sub>). A  
15 suitable solvent is, for example, an aprotic solvent such as a halogenated aliphatic hydrocarbon (such as dichloromethane or trichloroethylene) or an optionally halogenated aromatic hydrocarbon such as toluene or halogenated toluene. The diphosphine of formula (Ia<sub>12</sub>)  
20 is recovered in aqueous phase.

Diphosphines of formula (Ia<sub>13</sub>) or (Ia<sub>14</sub>) that correspond to formula (I) or (I') in which X<sub>1</sub> and X<sub>2</sub> represent, respectively, a group -NHR<sub>a</sub> or a group -N(R<sub>a</sub>)<sub>2</sub> are  
25 obtained by reacting, respectively, the diphosphine in dioxide and dihalo form of formula (IIa<sub>1</sub>) and an amine R<sub>a</sub>NH<sub>2</sub> or (R<sub>a</sub>)<sub>2</sub>NH (Kazankov M.V., Ginodman L.G., J. Organic. Chem., USSR, 1975, 11, 451) followed by reduction of the diphosphine in dioxide form as  
30 described above.

A diphosphine of formula (Ia<sub>15</sub>) that corresponds to formula (I) or (I') in which X<sub>1</sub> and X<sub>2</sub> represent a group -N=CH-R<sub>a</sub> is obtained by reacting ammonia with the  
35 diphosphine in dioxide and dihalo form of formula (IIa<sub>1</sub>) followed by reaction of the amino group with a compound

of the type  $R_a\text{-CHO}$ , followed by reduction of the diphosphine in dioxide form as described above.

A diphosphine of formula ( $Ia_{16}$ ) that corresponds to  
 5 formula (I) or (I') in which  $X_1$  and  $X_2$  represent an  
 $\text{-NH-NH}_2$  group is obtained by reacting hydrazine with the  
 diphosphine in dioxide and dihalo form of formula ( $IIa_1$ )  
 (Kazankov M.V., Ginodman L.G., *J. Org. Chem., USSR*,  
 1975, 11, 451) followed by reduction of the diphosphine  
 10 in dioxide form as described above.

A diphosphine of formula ( $Ia_{17}$ ) that corresponds to  
 formula (I) or (I') in which  $X_1$  and  $X_2$  represent an  
 $\text{-N=N}^+=\text{N}^-$  group is obtained by reacting  $\text{HN}_3$  or  $\text{NaN}_3$  with  
 15 the diphosphine in dioxide and dihalo form of formula  
 ( $IIa_1$ ) (Scriven E.F.V., Turnbull K., *Chem. Rev.*, 1988,  
 88, 297) followed by reduction of the diphosphine in  
 dioxide form as described above.

20 A diphosphine of formula ( $Ia_{18}$ ) that corresponds to  
 formula (I) or (I') in which  $X_1$  and  $X_2$  represent an  
 $\text{-N=C=O}$  group is obtained by reacting the compound of  
 formula ( $Ia_{13}$ ) with phosgene, performed according to the  
 teaching of the literature, especially by Jerry March,  
 25 *Advanced Organic Chemistry*, 5th Edition, John Wiley and  
 Sons, p. 507.

As a variant, the invention also provides a diphosphine  
 of formula ( $Ia_{19}$ ) in which  $X_1$  and  $X_2$  represent a  
 30 hydrocarbon-based group R chosen from alkyl, alkenyl,  
 alkynyl, cycloalkyl, aryl and arylalkyl groups and  
 which is obtained by preparing the organomagnesium  
 reagent corresponding to the dihalo diphosphine ( $IIa_1$ )  
 in dioxide form by reacting the latter with magnesium,  
 35 followed by reaction of the reagent obtained with the  
 halogenated hydrocarbon  $R\text{-X}_0$  ( $X_0 = \text{Br or Cl}$ ) (Kharasch

M.S., Reinmuth O., *Grignard reactions of nonmetallic substances*; Prentice-Hall: Englewood Cliffs, NJ, 1954, 5). A reduction of the diphosphine in dioxide form is then performed as described above.

5

As a variant, the invention also provides a diphosphine of formula (Ia<sub>20</sub>) in which X<sub>1</sub> and X<sub>2</sub> represent an alkyl group substituted with one or more halogen atoms, especially with fluorine atoms. It is preferably a  
10 perfluoroalkyl group of the type -(CH<sub>2</sub>)<sub>p</sub>F<sub>q</sub> in which p is between 1 and 15 and preferably between 6 and 10, and q is between 3 and 21 and preferably between 13 and 25.

The production of such a diphosphine is obtained by  
15 reacting the diphosphine in dioxide and dihalo form of formula (IIa<sub>1</sub>) with the corresponding iodo species I(CH<sub>2</sub>)<sub>p</sub>F<sub>q</sub>, p and q having the meanings given above, in the presence of copper, optionally a base, and a polar solvent.

20

The ratio between the number of moles of diphosphine of formula (IIa<sub>1</sub>) and the number of moles of iodoperfluoro compound ranges between 1 and 5 and preferably between 1 and 3.

25

The ratio between the number of moles of copper and the number of moles of dibromo diphosphine ranges between 5 and 10.

30 As regards the base, use is made of a trapping base especially such as those mentioned above, in particular bipyridine.

The ratio between the number of moles of base and the  
35 number of moles of dibromo diphosphine ranges between 0.1 and 1.

The reaction advantageously takes place in a polar solvent, for instance dimethyl sulfoxide, dimethylformamide or fluorobenzene.

- 5 The reaction takes place between 60°C and 100°C and preferably between 70°C and 80°C.

The reaction lasts between 24 and 36 hours.

- 10 At the end of reaction, the mixture is diluted with a solvent (for example dichloromethane), the copper is separated out by filtration and the organic phase is recovered, which is conventionally washed with water and then with a dilute acid solution (for example 1N  
15 HCl) and then with sodium hydrogen carbonate.

The organic phase is dried and the solvent is then removed by evaporation.

- 20 The diphosphine in dioxide form containing perfluoroalkyl groups in positions 5 and 5' is recovered. A reduction of the diphosphine in dioxide form is then performed as described above.

- 25 As a variant, the invention also provides a diphosphine of formula (Ia<sub>21</sub>) in which X<sub>1</sub> and X<sub>2</sub> represent a hydroxyl group. It is obtained from the diphosphine in dioxide and dihalo form of formula (IIa<sub>1</sub>), according to an aromatic nucleophilic substitution with OH<sup>-</sup> [Fyfe, C.A.  
30 in Patai *The Chemistry of the hydroxyl group*, Pt. 1, Wiley: NY, 1971, p. 83]. A reduction of the diphosphine in dioxide form is then performed as described above.

- The invention also provides a diphosphine of formula  
35 (Ia<sub>22</sub>) in which X<sub>1</sub> and X<sub>2</sub> represent a group -OCOR<sub>a</sub>. It is obtained from the diphosphine of formula (Ia<sub>17</sub>) by

reaction with the carboxylic acid  $R_a\text{COOH}$  or a derivative (halide or anhydride), according to a standard esterification reaction.

- 5 The process of the invention may be performed starting with an optically active compound of formula (IV) with conservation of the chirality from the start to the end of the synthesis.
- 10 Thus, starting with (*S*)-BINAP, (*S*)-5,5'-diaminomethyl-2,2'-bis(diphenylphosphino)-1,1'-binaphthyl is obtained. Starting with (*R*)-BINAP, (*R*)-5,5'-diaminomethyl-2,2'-bis(diphenylphosphino)-1,1'-binaphthyl is obtained.

15

According to another aspect of the invention, the invention relates to the use of diphosphine in which the naphthyl groups are substituted in the 5,5' position with two identical functional groups capable of  
 20 reacting with polymerizable monomers, leading to a racemic or optically active polymer.

The diphosphines used correspond to formula (I').

- 25 In formula (I'),  $X_1$  represents an aminomethyl group  $-\text{CH}_2-\text{NH}_2$ , a hydroxyl group  $-\text{OH}$ , a hydroxymethyl group  $-\text{CH}_2-\text{OH}$ , a carboxylic or ester group  $-\text{COOR}_a$  ( $R_a$  represents a hydrogen atom or an alkyl, cycloalkyl, arylalkyl or phenyl group, more preferably a hydrogen atom or a  $\text{C}_1$ - $\text{C}_2$  alkyl group), an isocyanato group  $-\text{N}=\text{C}=\text{O}$   
 30 or an isocyanatomethyl group  $-\text{CH}_2-\text{N}=\text{C}=\text{O}$ .

Advantageously, they are diphosphines corresponding to formulae ( $\text{Ia}_{21}$ ), ( $\text{Ia}_3$ ), ( $\text{Ia}_4$ ), ( $\text{Ia}_5$ ), ( $\text{Ia}_6$ ), ( $\text{Ia}_{11}$ ) and  
 35 ( $\text{Ia}_{18}$ ).



Another subject of the invention thus lies in optically active polymers comprising the chiral diphosphine of formula (I') as polymer units.


- 5 Another subject of the invention consists of the use of the optically active polymer as a ligand in the preparation of metal complexes for asymmetric catalysis.
- 10 The polymer of the invention consists of a sequence of two types of units.

The first type of unit is the chiral diphosphine residue corresponding to formula (I') and bearing two  
15 identical polymerizable functional groups.

The second type of unit is a monomer residue that is polymerizable with said functional groups, i.e. a monomer comprising at least two identical functional  
20 groups capable of reacting with the functional groups of the chiral diphosphine.

The preferred monomer is difunctional and may be represented by formula (X) below:

25



in which:

- M represents a divalent hydrocarbon-based group of aliphatic, alicyclic and/or aromatic nature,
- 30 -  $Y_1$  represents a functional group, preferably a carboxylic, ester, hydroxyl, amino, isocyanato, aldehyde or ketone group.


- 35 The size of the group M will be adjusted by a person skilled in the art as a function of the final use of

the ligand and especially as a function of the reaction that the metal complex formed from this polymer ligand is intended to catalyze.

- 5 Preferred meanings will be given later for the reagents preferentially chosen.

It will be pointed out that the monomers most often used correspond to formula (X) in which M represents a  
 10 C<sub>1</sub>-C<sub>12</sub> and preferably C<sub>1</sub>-C<sub>6</sub> alkylene chain; a cycloalkylene and preferably a cyclohexylene group; an arylene group, preferably phenylene, tolylene or naphthalene.

- 15 Thus, the optically active polymer resulting from the polymerization of the diphosphine of formula (I') and of the monomer of formula (X) comprises the following repeating unit:



20

in which

- R<sub>1</sub> and R<sub>2</sub>, which may be identical or different, represent a hydrogen atom or a substituent,
- 25 - Ar<sub>1</sub> and Ar<sub>2</sub> independently represent an alkyl, alkenyl, cycloalkyl, aryl or arylalkyl group,

- M represents a divalent hydrocarbon-based group of aliphatic, alicyclic and/or aromatic nature;
- F<sub>1</sub> represents a functional group resulting from the reaction:
  - 5     . of the group X<sub>1</sub> chosen from the following groups: aminomethyl, hydroxyl, hydroxymethyl, carboxylic, ester, isocyanato, isocyanatomethyl, and of the group Y<sub>1</sub> chosen from carboxylic, ester, hydroxyl, amino, isocyanato, aldehyde and
  - 10     ketone groups,
- the degree of polymerization is preferably between 2 and 100 and better still between 2 and 50.

The choice of these functions, combined with the choice  
 15 of the polymerizable monomers, determines the nature of the resulting polymer.

Thus, F<sub>1</sub> more particularly represents:

- a urea group (F<sub>1</sub>) resulting from the reaction of an  
 20     aminomethyl group (X<sub>1</sub>) with an isocyanato group (Y<sub>1</sub>) or an isocyanato or isocyanatomethyl group (X<sub>1</sub>) with an amino group (Y<sub>1</sub>),
- a urethane group (F<sub>1</sub>) resulting from the reaction of an isocyanato or isocyanatomethyl group (X<sub>1</sub>)  
 25     with a hydroxyl group (Y<sub>1</sub>) or a hydroxyl or hydroxymethyl group (X<sub>1</sub>) with an isocyanato group (Y<sub>1</sub>),
- an ester group (F<sub>1</sub>) resulting from the reaction of a carboxylic or ester group (X<sub>1</sub>) with a hydroxyl  
 30     group (Y<sub>1</sub>) or a hydroxyl or hydroxymethyl group (X<sub>1</sub>) with a carboxylic or ester group (Y<sub>1</sub>),
- an amide group (F<sub>1</sub>) resulting from the reaction of a carboxylic group (X<sub>1</sub>) with an amino group (Y<sub>1</sub>) or  
 35     an aminomethyl group (X<sub>1</sub>) with a carboxylic group (Y<sub>1</sub>),
- an imine group (F<sub>1</sub>) resulting from the reaction of

an aminomethyl group ( $X_1$ ) with an aldehyde or ketone group ( $Y_1$ ).

5 The present invention encompasses all types of polymers and especially linear, branched or crosslinked polymers. Mention may be made of polymers such as polyester, polyurethane, polyamide, polyurea, polyimine and polyimide.

10 The preferred polymers are linear polymers, but the invention does not exclude crosslinked polymers obtained by using a polymerizable monomer comprising more than two functional groups, for example three groups.

15 The choice of monomers placed in contact will be made as a function of their ease of access.

Thus, the invention favors the chiral substance bearing  
20 in position 5,5' two aminomethyl groups.

The compounds preferably used, corresponding to formula ( $Ia_3$ ) in which  $Ar_1$  and  $Ar_2$  are independently chosen from a ( $C_1$ - $C_4$ )alkyl group or a phenyl group optionally  
25 substituted with methyl or tert-butyl; and ( $C_5$ - $C_6$ )-cycloalkyl optionally substituted with methyl or tert-butyl.

Those of formula ( $Ia_3$ ) in which  $Ar_1$  and  $Ar_2$  are  
30 identical and represent a phenyl group are more preferably chosen.

In accordance with the invention, one of the diphosphines corresponding to one of the formulae ( $I'$ ) is  
35 reacted with a polymerizable monomer. It is preferably chosen to use only one polymerizable monomer.

Classes of monomers that may especially be mentioned include diacids, diesters, diols, diisocyanates, dialdehydes and diketones.

5

Although the invention is not intended to be specifically limited thereto, polyamides, polyureas and polyimides will be described in further detail.

- 10 The polyureas, polyamides and polyimides of the invention may be prepared starting with a chiral diphosphine consisting of a chiral substance bearing, as functional groups, two aminomethyl groups, and which corresponds to the formulae (Ia<sub>3</sub>).

15


#### Polyureas

- When the targeted polymer is a polyurea, it may be synthesized by polymerization of a diphosphine bearing  
20 two -CH<sub>2</sub>-NH<sub>2</sub> groups with one or more di- or polyisocyanates.

The nature of the isocyanate compound is not critical per se.

25

Preferably, the diisocyanate is a diisocyanate of formula (Xa):



30

in which:

- J represents a divalent hydrocarbon-based group of aliphatic, alicyclic and/or aromatic nature.

- 35 The size of the group J will be adjusted by a person skilled in the art as a function of the final use of

the ligand and especially as a function of the reaction that the metal complex formed from this polymer ligand is intended to catalyze.

- 5 The catalytic sites of the polymer of the invention are located on the diphosphine-based units. The size of the group J thus determines the spacing of the catalytic sites.
- 10 The group J is, for example, a  $C_1$ - $C_{16}$  and preferably  $C_1$ - $C_{12}$  alkylene chain, optionally interrupted with one or more (preferably 1 to 4 and better still 1 to 2) hetero atoms chosen from O, N and S, said chain optionally comprising one or more unsaturations (preferably 1 to
- 15 4 and better still 1 to 2); a group  $-(CH_2)_a-K-(CH_2)_b-$  in which a and b are, independently, an integer from 0 to 6 and K represents  $(C_6-C_8)$ cycloalkylene; a group  $-(CH_2)_a-L-(CH_2)_b-$  in which a and b are as defined above and L represents  $(C_6-C_{10})$ arylene; a group
- 20  $-(CH_2)_a-V_o-(CH_2)_b-$  in which a and b are as defined above and  $V_o$  represents a 5- to 8-membered heteroarylene comprising 1 to 3 hetero atoms chosen from O, N and S; or alternatively a group  $-M_o-Q-M_o-$  in which  $M_o$  is chosen from  $(C_3-C_8)$ cycloalkylene and  $(C_6-C_{10})$ arylene and Q represents
- 25 a bond, a sulfur atom, an oxygen atom,  $(C_1-C_4)$ alkylene,  $-SO-$ ,  $-SO_2-$  or  $-CO-$ .

When J contains an alkylene chain, it is linear or branched and preferably contains 1 to 6 carbon atoms.

- 30 When this alkylene chain comprises a nitrogen atom, it bears a  $(C_1-C_6)$ alkyl group or a hydrogen atom.

When J contains cycloalkylene, J is preferably cyclohexylene.

35

When J contains arylene, J is preferably phenylene or

naphthalene.

When J represents  $-(CH_2)_a-L-(CH_2)_b-$ ,  $-(CH_2)_a-K-(CH_2)_b-$  or  $-(CH_2)_a-V_O-(CH_2)_b-$ , a and b are preferably identical.

5

The term "heteroarylene" means a divalent group corresponding to a heterocycle in which two hydrogen atoms have been replaced with two bonds.

10 Heteroarylenes derived from the following heterocycles are preferred: furan, thiophene, pyrrole, oxazole, thiazole, imidazole, pyrazole, isoxazole, isothiazole, pyridine, pyridazine, pyrimidine, pyrazine, indolizine, indole, isoindole, benzofuran, benzothiophene, benzim-  
15 idazole, benzothiazole, quinoline, isoquinoline, cinnoline, phthalazine, quinazoline, naphthyridine and pteridine. The heteroarylene is very advantageously derived from imidazole, benzimidazole, pyrimidine or quinazoline.

20

When J represents  $-M_O-Q-M_O-$ , Q is preferably  $(C_1-C_2)$ alkylene or a bond, and  $M_O$  is preferably cyclohexylene or phenylene.

25 The group J as defined above may bear one or more substituents chosen from a halogen atom, a  $C_1-C_6$  alkyl group, a  $C_1-C_6$  alkoxy group, an oxo group and a  $di(C_1-C_6)$ alkylamino group.

30 Examples of diisocyanates that are particularly suitable are:

- 1,2-diisocyanatopropane,
- 1,4-diisocyanatobutane
- 2,6-diisocyanatotoluene,
- 35 - 1,12-diisocyanatododecane,
- trans-1,4-cyclohexanediisocyanate,

- 4,4'-diisocyanatodiphenylmethane,
- 4,4'-diisocyanato-3,3'-dimethyldiphenylmethane,
- 1,5-diisocyanatonaphthalene.

5 The condensation of the diisocyanate with the diphosphine is performed under suitable conditions that are readily determined by a person skilled in the art.

These polymerization conditions are preferably adjusted  
10 so as to obtain a polymer with a degree of polymerization of from 2 to 100, preferably from 5 to 100, for example from 2 to 50 and better still from 4 to 25.

15 Polyureas with a degree of polymerization of from 3 to 8 are particularly suitable for use.

A person skilled in the art will select the degree of polymerization such that the resulting polymer is  
20 insoluble in the solvent or mixture of solvents used in the asymmetric reaction that needs to be catalyzed.

The choice of the polymerization method is not critical according to the invention.

25 One particularly suitable method is solution polymerization.

The solvent is generally a polar aprotic solvent chosen  
30 from an optionally halogenated aliphatic hydrocarbon, for example methylene chloride, chloroform, carbon tetrachloride or 1,2-dichloroethane; an optionally halogenated aromatic hydrocarbon, for example chlorobenzene or dichlorobenzene; an ether such as diethyl  
35 ether, diisopropyl ether, tetrahydrofuran, dioxane, diethylene glycol dimethyl ether and glymes, and



especially 1,2-dimethoxyethane; an amide such as formamide, dimethylformamide, dimethylacetamide, N-methyl-2-pyrrolidinone or hexamethylphosphorylamide; a nitrile such as acetonitrile or isobutyronitrile; and  
5 dimethyl sulfoxide.

The concentration of reagents in the solution varies very widely as a function of the solubility of the reagents. It is generally between 0.05 and 1 mol/l and  
10 preferably between 0.01 and 1 mol/l, for example 0.1 mol/l.

Preferably, the diisocyanate is used in slight excess relative to the diphosphine, although, strictly speaking,  
15 ing, a stoichiometric ratio of these two compounds may be suitable.

Thus, the molar ratio of the diisocyanate to the diphosphine is generally set at between 1 and 1.5, for  
20 example between 1 and 1.3.

The temperature at which the polymerization is performed is determined as a function of the reactivity of the various reagents and of the desired degree of  
25 polymerization. As a guide, the temperature ranges between -20°C and 100°C, preferably between room temperature and 100°C, for example between 15 and 100°C and better still between 15 and 40°C. It is advantageously 20°C.


30

The polymerization is performed conventionally by dissolving the reagents in the solvent, mixing, optionally heating the reaction medium, and then isolating the polymer, for example by filtration of the reaction  
35 medium. It will be noted that it may be necessary, before isolation of the polymer, to deactivate the ends

of the polymer chain, and especially the unreacted isocyanate functions, by addition of a C<sub>1</sub>-C<sub>6</sub> alkanol, for example propanol, isopropanol, methanol or ethanol, or even tert-butyl alcohol.

5

An example of a polymer that is particularly preferred is a polymer containing as repeating unit:



10

in which

- R<sub>1</sub> and R<sub>2</sub>, which may be identical or different, represent a hydrogen atom or a substituent,
- Ar<sub>1</sub> and Ar<sub>2</sub> independently represent an alkyl, alkenyl, cycloalkyl, aryl or arylalkyl group,
- J has the meaning given above,
- the degree of polymerization is preferably between 2 and 100 and better still between 2 and 50.

## 20 Polyamides

When the polymer is a polyamide, it may be prepared by condensation of a chiral diphosphine bearing two aminomethyl functions with one or more dicarboxylic acids or activated derivatives thereof.

The dicarboxylic acid advantageously corresponds to formula (Xb) below:



in which W is as defined for J above.

- 5 The preferred meanings of J indicated above are also preferred meanings of W.

The group W may be substituted with one or more halogen atoms or oxo, (C<sub>1</sub>-C<sub>6</sub>)alkyl, (C<sub>1</sub>-C<sub>6</sub>)alkoxy or di(C<sub>1</sub>-C<sub>6</sub>)-  
10 alkylamino groups.

Among these dicarboxylic acids, the following are preferred:

- the aliphatic acids chosen from:
  - 15 - malonic acid,
  - succinic acid,
  - glutaric acid,
  - adipic acid,
  - 2,4-dimethyladipic acid,
  - 20 - pimelic acid,
  - suberic acid,
  - azelaic acid,
  - sebacic acid,
  - dodecanedioic acid,
  - 25 - fumaric acid,
  - maleic acid,
  - methyliminodiacetic acid,
  - 3-dimethylaminohexanedioic acid,
  - cycloalkanedicarboxylic acids and especially:
    - 30 - 1,4-cyclohexanedicarboxylic acid,
  - the aromatic dicarboxylic acids chosen from:
    - phthalic acid,
    - isophthalic acid,
    - terephthalic acid,
    - 35 - phenylenediacetic acid,
    - 1,5-naphthalenedicarboxylic acid,

- 4,4'-diphenyldicarboxylic acid,
- 3,3'-diphenyldicarboxylic acid,
- 4,4'-dicarboxydiphenyl sulfone,
- 3,3'-dicarboxydiphenyl sulfone.

5

One particularly preferred group of dicarboxylic acids consists of the following acids:

- succinic acid,
- adipic acid,
- 10 - fumaric acid,
- isophthalic acid,
- terephthalic acid,
- 1,5-naphthalenedicarboxylic acid,
- 4,4'-diphenyldicarboxylic acid,
- 15 - 3,3'-diphenyldicarboxylic acid.

The activated derivative of the dicarboxylic acid more generally denotes the dicarboxylic acid compound in which one or two of the carboxylic functions have been  
20 modified so as to increase their reactivity.

Activated derivatives of dicarboxylic acid are obtained, for example, by formation of an anhydride bond or of a group -COY in which Y is a halogen atom  
25 such as bromine or chlorine.

Other activated derivatives of dicarboxylic acids are those bearing, instead of the carboxylic functions, groups -COT in which T denotes an azide, imidazolidine,  
30 p-nitrophenoxy, 1-benzotriazole, N-O-succinimide, acyloxy (such as pivaloyloxy), (C<sub>1</sub>-C<sub>4</sub> alkoxy)carbonyloxy, or dialkyl- or dicycloalkyl-O-ureide group.

The condensation of the diphosphine with the  
35 dicarboxylic acid or the activated derivative thereof is generally performed in a solvent.

When the dicarboxylic acid is used in unmodified form, it may be advantageous to perform the condensation in the presence of a catalyst, for example a strong acid such as hydrochloric acid or sulfuric acid, or alternatively in the presence of a coupling agent such as those commonly used in peptide synthesis.

Among the known coupling agents that may be mentioned are N-hydroxylated derivatives such as N-hydroxy-succinimide and 1-hydroxybenzotriazole; disulfides such as dipyridyl 2,2'-disulfide; succinic acid derivatives such as N,N'-disuccinimidyl carbonate; phosphinic chlorides such as N,N'-bis(2-oxo-3-oxazolidinyl)phosphinic chloride; oxalates such as N,N'-disuccinimidyl oxalate (DSO), diphthalimide N,N'-oxalate (DPO), N,N'-bis(norbornenylsuccinimidyl) oxalate (BNO), 1,1'-bis(benzotriazolyl) oxalate (BBTO), 1,1'-bis(6-chlorobenzotriazolyl) oxalate (BCTO) or 1,1'-bis(6-trifluoromethylbenzotriazolyl) oxalate (BTBO); triarylphosphines such as triphenylphosphine; a combination of a di(lower alkyl) azodicarboxylate and of a triarylphosphine, such as a combination of diethyl azodicarboxylate and of triphenylphosphine; N-(lower alkyl)-5-aryl-isoxazolium-3'-sulfonates such as N-ethyl-5-phenylisoxazolium-3'-sulfonate; carbodiimide derivatives, including N',N'-dicycloalkylcarbodiimides such as N',N'-dicyclohexylcarbodiimide (DCC) or 1-ethyl-3-(3-dimethylaminopropyl)carbodiimide (EDAPC); diheteroaryl diselenides such as di-2-pyridyl diselenide; arylsulfonyltriazo-  
 azolides such as p-nitrobenzenesulfonyltriazo-  
 2-halo-1-(lower alkyl)pyridinium halides such as 2-chloro-1-methylpyridinium iodide; diarylphosphorylazides such as diphenylphosphorylazide (DPPA); imidazole derivatives such as 1,1'-oxalyldiimidazole or N,N'-carbonyldiimidazole; benzotriazole derivatives such as 1-hydroxybenzotriazole (HOBT); and dicarbox-

imide derivatives such as N-hydroxy-5-norbornene-2,3-dicarboximide (HONB). Among these, carbodiimide derivatives are preferred.

- 5 The reaction may take place within a wide temperature range.

According to the reactivity of the reagents used, the reaction temperature ranges between -20°C and 100°C.

10

When the polymerization involves the reaction of an activated derivative of the dicarboxylic acid with a diphosphine, a relatively low temperature, preferably of between 0°C and 40°C, is sufficient.

15

Conversely, when the dicarboxylic acid is used in unmodified form in the reaction, the temperature is preferably between 50 and 80°C.

- 20 The concentration of reagents in the reaction medium is not a determining factor according to the invention. It may range between 0.05 and 1 mol/l.

In general, the molar ratio of the dicarboxylic acid or  
25 of the activated derivative thereof to the diphosphine ranges between 0.8 and 1.5 and preferably between 0.9 and 1.2.

A typical procedure, illustrating the preparation of a  
30 polyamide starting with a carboxylic acid chloride, is as follows.

3.75 mmol of the carboxylic acid chloride are added to a solution of 4.16 mmol of diphosphine in 5 ml of N,N-dimethylacetamide. The reaction mixture is stirred  
35 overnight at room temperature (18 to 30°C). The poly-


amide is then precipitated from 150 ml of distilled water. The polymer is filtered off on a sinter funnel, and washed with water and then with isopropanol.

5 The general conditions for performing the polymerization and for isolating the polymer will be readily determined by a person skilled in the art, given that the preferred polyamides of the invention have a degree of polymerization of between 2 and 100,  
 10 for example between 5 and 100, preferably between 2 and 50 and better still between 4 and 25.

A person skilled in the art will select the degree of polymerization such that the resulting polymer is  
 15 insoluble in the solvent or mixture of solvents used in the asymmetric reaction that needs to be catalyzed.

An example of a preferred polymer is a polymer containing as repeating unit:

20



in which

- R<sub>1</sub> and R<sub>2</sub>, which may be identical or different,  
 25 represent a hydrogen atom or a substituent,
- Ar<sub>1</sub> and Ar<sub>2</sub> independently represent an alkyl, alkenyl, cycloalkyl, aryl or arylalkyl group,
- W has the meaning given for J,

- the degree of polymerization is preferably between 2 and 100 and better still between 2 and 50.

### Polyimides

5

When the polymer is a polyimide, it may be prepared by condensation of a diphosphine bearing two aminoethyl functions with one or more tetracarboxylic acids or tetracarboxylic acid dianhydrides.

10

For the preparation of these polyimides, a person skilled in the art may take inspiration from D.C. Sherrington, Chem. Commun., 1998, 2275-2286.

- 15 Advantageously, the polyimides are prepared in two steps.

In a first step, a polyamide is formed. This step is performed, for example, at a temperature of between 15 and 50°C and preferably between 20 and 30°C, in a polar aprotic solvent (such as an amide such as formamide, dimethylacetamide or N-methyl-2-pyrrolidinone, preferably dimethylacetamide).

- 25 In a second step, the polyimide is formed. This second step may be performed by treatment with a mixture of acetic anhydride and pyridine at a temperature of between -100°C and 10°C and preferably between -78°C and -50°C.

30

According to another variant of the invention, the polymer may be a polyurethane.

### Polyurethanes

35

When the polymer is a polyurethane, it may be prepared



by condensation of a chiral diphosphine bearing two hydroxyl or hydroxymethyl groups with a monomer of the diisocyanate type.

- 5 In this case, a catalysis with a tin salt is often necessary. Reference may be made especially to the article by M. Lemaire et al. *J. Mol. Cat. A.* 2002, Vol. 182-183, 239-247.
- 10 According to one of its aspects, the invention thus relates to a process for preparing a polymer of the invention, comprising the polymerization of a chiral diphosphine of formula (I') with one or more polymer-  
15 phosphine consisting of a chiral substance bearing two identical functional groups capable of reacting with said polymerizable monomers.

The invention also relates to the racemic polymer  
20 corresponding to the optically active polymer of the invention.

This polymer may be prepared simply by polymerization of the appropriate diphosphine with one or more  
25 polymerizable monomers, said diphosphine bearing two identical functional groups capable of reacting with said polymerizable monomers.

Preferably, the diphosphines used in this reaction are  
30 racemic diphosphines corresponding to the preferred chiral diphosphines defined above. Thus, according to one preferred embodiment of the invention, the racemic diphosphine consists of a racemic base skeleton of formula (I') bearing two identical functional groups.

35 Similarly, the polymerizable monomers preferably used

for this polymerization are those described above for the preparation of the optically active polymers.

The operating conditions for this polymerization will  
5 be readily determined by a person skilled in the art by analogy with those proposed for the polymerization reaction leading to the optically active polymer.

The diphosphines obtained according to the processes of  
10 the invention and those that are insolubilized in the form of a polymer as described above may be used as ligands in the preparation of metal complexes for the asymmetric catalysis of the following reactions: hydrogenation, hydrosilylation, hydroboration of unsaturated  
15 compounds, epoxidation of allylic alcohols, vicinal hydroxylation, hydrovinylation, hydroformylation, cyclopropanation, olefin isomerization, propylene polymerization, addition of organometallic compounds to aldehydes, allylic alkylation, reactions of aldol type,  
20 Diels-Alder reactions and, in general, reactions for formation of C-C bonds (such as allylic substitutions or Grignard cross-couplings).

According to one preferred embodiment of the invention,  
25 the complexes are used for the hydrogenation of C=O, C=C and C=N bonds.

One subject of the invention is thus novel complexes comprising the chiral diphosphine of the invention or  
30 the optically active polymer as defined above and a transition metal.

As examples of transition metals capable of forming complexes, mention may be made especially of metals  
35 such as rhodium, ruthenium, rhenium, iridium, cobalt, nickel, platinum and palladium.

Among the abovementioned metals, rhodium, ruthenium and iridium are preferred.


5 Thus, according to another of its aspects, the invention relates to the use of diphosphine optionally in insoluble form for the preparation of a metal complex of a transition metal intended for asymmetric catalysis, and more especially of a ruthenium, iridium  
10 or rhodium complex.

Specific examples of said complexes of the present invention are given hereinbelow, without any limiting nature.

15

In the following formulae, P represents a ligand according to the invention, i.e. diphosphine or diphosphine insolubilized in the form of a polymer.

20 A preferred group of rhodium and iridium complexes is defined by the formula:



25 in which:

- P represents a ligand according to the invention;
- Y<sub>1</sub> represents an anionic coordinating ligand;
- Me represents iridium or rhodium; and
- Lig represents a neutral ligand.

30

Among these compounds, the ligands that are particularly preferred are those in which:

- Lig represents an olefin containing from 2 to 12 carbon atoms;
- 35 - Y<sub>1</sub> represents an anion PF<sub>6</sub><sup>-</sup>, PCl<sub>6</sub><sup>-</sup>, BF<sub>4</sub><sup>-</sup>, BCl<sub>4</sub><sup>-</sup>, SbF<sub>6</sub><sup>-</sup>, SbCl<sub>6</sub><sup>-</sup>, BPh<sub>4</sub><sup>-</sup>, ClO<sub>4</sub><sup>-</sup>, CN<sup>-</sup>, CF<sub>3</sub>SO<sub>3</sub><sup>-</sup>, halogen,


preferably  $\text{Cl}^-$  or  $\text{Br}^-$ , a 1,3-diketonate, alkyl-carboxylate or haloalkylcarboxylate anion with a lower alkyl (preferably of  $\text{C}_1\text{-C}_6$ ) group, a phenyl-carboxylate or phenoxide anion in which the  
 5 benzene ring may be substituted with lower alkyl (preferably  $\text{C}_1\text{-C}_6$ ) groups and/or halogen atoms.

In formula ( $\text{F}_1$ ),  $\text{Lig}_2$  may represent two ligands Lig as defined above or a bidentate ligand such as a linear or  
 10 cyclic, polyunsaturated bidentate ligand comprising at least two unsaturations.

It is preferable according to the invention for  $\text{Lig}_2$  to represent 1,5-cyclooctadiene or norbornadiene, or for  
 15 Lig to represent ethylene.

The term "lower alkyl groups" generally means a linear or branched alkyl group containing from 1 to 4 carbon atoms.

20 Other iridium complexes are those of formula:



25 in which Lig, P and  $\text{Y}_1$  are as defined for formula ( $\text{F}_1$ ).

A preferred group of ruthenium complexes consists of the compounds of formula:




in which:

- P represents a ligand according to the invention;
- 35 -  $\text{Y}_1^1$  and  $\text{Y}_1^2$ , which may be identical or different, represent an anion  $\text{PF}_6^-$ ,  $\text{PCl}_6^-$ ,  $\text{BF}_4^-$ ,  $\text{BCl}_4^-$ ,  $\text{SbF}_6^-$ ,

$\text{SbCl}_6^-$ ,  $\text{BPh}_4^-$ ,  $\text{ClO}_4^-$ ,  $\text{CF}_3\text{SO}_3^-$ , a halogen atom, more particularly chlorine or bromine, or a carboxylate anion, preferably acetate or trifluoroacetate.

- 5 Other ruthenium complexes are those corresponding to formula XIV below:



10 in which:

- P represents a ligand according to the invention;
- ar represents benzene, p-methylisopropylbenzene or hexamethylbenzene;
- $\text{Y}_1^3$  represents a halogen atom, preferably chlorine or bromine;
- 15 -  $\text{Y}_1^4$  represents an anion, preferably a  $\text{PF}_6^-$ ,  $\text{PCl}_6^-$ ,  $\text{BF}_4^-$ ,  $\text{BCl}_4^-$ ,  $\text{SbF}_6^-$ ,  $\text{SbCl}_6^-$ ,  $\text{BPh}_4^-$ ,  $\text{ClO}_4^-$  or  $\text{CF}_3\text{SO}_3^-$  anion.

- 20 It is also possible to use in the process of the invention complexes based on palladium and platinum.

As more specific examples of said complexes, mention may be made, inter alia, of  $\text{Pd}(\text{hal})_2\text{P}$  and  $\text{Pt}(\text{hal})_2\text{P}$  in  
 25 which P represents a ligand according to the invention and hal represents halogen, for instance chlorine.

The complexes comprising a ligand according to the invention and the transition metal may be prepared  
 30 according to the known processes described in the literature.

The complexes are generally prepared from a pre-catalyst, the nature of which varies according to the  
 35 transition metal selected.

In the case of rhodium complexes, the precatalyst is, for example, one of the following compounds:  $[\text{Rh}^{\text{I}}(\text{CO})_2\text{Cl}]_2$ ;  $[\text{Rh}^{\text{I}}(\text{COD})\text{Cl}]_2$  in which COD denotes cyclo-octadiene; or  $\text{Rh}^{\text{I}}(\text{acac})(\text{CO})_2$  in which acac denotes  
 5 acetylacetonate.

In the case of ruthenium complexes, precatalysts that are particularly suitable are bis(2-methylallyl)cyclo-octa-1,5-dieneruthenium and  $[\text{RuCl}_2(\text{benzene})]_2$ . Mention  
 10 may also be made of  $\text{Ru}(\text{COD})(\eta^3-(\text{CH}_2)_2\text{CHCH}_3)_2$ .

By way of example, starting with bis(2-methylallyl)-cycloocta-1,5-dieneruthenium, a solution or suspension containing the metal precatalyst, a ligand and a fully  
 15 degassed solvent such as acetone (the ligand concentration of the solution or suspension ranging between 0.001 and 1 mol/l) is prepared, to which is added a methanolic solution of hydrobromic acid. The ratio of the ruthenium to bromine advantageously ranges between  
 20 1:1 and 1:4 and preferably between 1:2 and 1:3. The molar ratio of the ligand to the transition metal is about 1. It may be between 0.8 and 1.2.

When the precatalyst is  $[\text{RuCl}_2(\text{benzene})]_2$ , the complex  
 25 is prepared by mixing together the precatalyst, the ligand and an organic solvent and optionally maintaining at a temperature of between 15 and 150°C for 1 minute to 24 hours and preferably from 30 to 120°C for 10 minutes to 5 hours.

30 Solvents that may be mentioned include aromatic hydrocarbons (such as benzene, toluene and xylene), amides (such as formamide, dimethylformamide, dimethylacetamide, N-methyl-2-pyrrolidinone or hexamethylphosphorylamide) and alcohols (such as ethanol, methanol,  
 35 n-propanol and isopropanol), and mixtures thereof.

Preferably, when the solvent is an amide, especially dimethylformamide, the mixture of the ligand, the precatalyst and the solvent is heated to between 80 and  
5 120°C.

As a variant, when the solvent is a mixture of an aromatic hydrocarbon (such as benzene) with an alcohol (such as ethanol), the reaction medium is heated to a  
10 temperature of between 30 and 70°C.

The catalyst is then recovered according to the standard techniques (filtration or crystallization) and is used in asymmetric reactions. However, the reaction  
15 that needs to be catalyzed by the complex thus prepared may be performed without intermediate isolation of the catalyst complex.

The case of hydrogenation is outlined in detail in the  
20 text hereinbelow.

The unsaturated substrate, dissolved in a solvent comprising the catalyst, is placed under hydrogen  
pressure.  
25

The hydrogenation is performed, for example, at a pressure ranging between 1.5 and 100 bar and at a temperature of between 20°C and 100°C.

30 The exact operating conditions depend on the nature of the substrate that needs to be hydrogenated. However, in the general case, a pressure of from 20 to 80 bar and preferably from 40 to 60 bar, and a temperature of from 30 to 70°C are particularly suitable.

35

The reaction medium may consist of the reaction medium

in which the catalyst was obtained. The hydrogenation reaction is then performed in situ.

As a variant, the catalyst is isolated from the  
5 reaction medium in which it was obtained. In this case, the reaction medium of the hydrogenation reaction consists of one or more solvents, chosen especially from C<sub>1</sub>-C<sub>5</sub> aliphatic alcohols, such as methanol or propanol, and an amide as defined above, preferably  
10 dimethylformamide, optionally as a mixture with benzene.

When the hydrogenation reaction is performed in situ, it is desirable to add to the reaction medium one or  
15 more solvents chosen from those mentioned above and more particularly one or more aliphatic alcohols.

According to one preferred embodiment, fully degassed methanol and the substrate are added to the reaction  
20 medium containing the complex. The amount of methanol, or more generally of solvent, that may be added is such that the concentration of the substrate in the hydrogenation reaction medium is between  $1 \times 10^3$  and 10 mol/l and preferably between 0.01 and 1 mol/l.

25 The molar ratio of the substrate to the catalyst generally ranges from 1/100 to 1/100 000 and preferably from 1/20 to 1/2000. This ratio is, for example, 1/1000.

30 The removal of the catalyst from the reaction medium is facilitated when the ligand used is in the form of a polymer.

The catalyst is separated from the reaction medium by  
35 nanofiltration or ultrafiltration.



The technique of nanofiltration is more particularly suitable in the case of catalysts of polymer type. The application of this technique is illustrated, for example, in Tetrahedron: Asymmetry, Vol. 8, No 12, 5 1975-1977, 1997.

One advantage of the process of the invention is that the recovered catalyst may be readily recycled without loss of activity.

10


The ruthenium, rhodium and iridium complexes prepared using the ligands of the invention are more especially suitable for the asymmetric catalysis of asymmetric hydrogenation reactions.

15

The ruthenium complexes prepared using the ligands of the invention are more especially suitable for the asymmetric catalysis of hydrogenation reactions of C=O bonds, C=N bonds and C=C bonds and preferably C=C bonds 20 of  $\alpha,\beta$ -ethylenic carboxylic acids.

As regards the hydrogenation of double bonds, the suitable substrates are of  $\alpha,\beta$ -unsaturated carboxylic acid type and/or derivatives of  $\alpha,\beta$ -unsaturated 25 carboxylic acids. These substrates are described in EP 95943260.0.

The  $\alpha,\beta$ -unsaturated carboxylic acid and/or the derivative thereof more particularly corresponds to 30 formula A:



in which:

- $R_1$ ,  $R_2$ ,  $R_3$  and  $R_4$  represent a hydrogen atom or any hydrocarbon-based group, insofar as:
  - 5     . if  $R_1$  is different than  $R_2$  and different than a hydrogen atom, then  $R_3$  may be any hydrocarbon-based group or functional group denoted by  $R$ ,
  - . if  $R_1$  or  $R_2$  represents a hydrogen atom and if  $R_1$  is different than  $R_2$ , then  $R_3$  is different than
  - 10    a hydrogen atom and different than  $-COOR_4$ ,
  - . if  $R_1$  is identical to  $R_2$  and represents any hydrocarbon-based group or functional group denoted by  $R$ , then  $R_3$  is different than  $-CH-(R)_2$  and different than  $-COOR_4$
  - 15    - one of the groups  $R_1$ ,  $R_2$  and  $R_3$  possibly representing a functional group.

A specific example that may be mentioned, inter alia, is 2-methyl-2-butenic acid.


20

A first group of preferred substrates is formed by the substituted acrylic acids that are precursors of amino acids and/or derivatives.

25 The term "substituted acrylic acids" means the set of compounds whose formula is derived from that of acrylic acid by substitution of at least two of the hydrogen atoms borne by the ethylenic carbon atoms with a hydrocarbon-based group or with a functional group.

30

They may be symbolized by the following chemical formula:




in which:

- $\text{R}_9$  and  $\text{R}'_9$ , which may be identical or different, represent a hydrogen atom, a linear or branched alkyl group containing from 1 to 12 carbon atoms, a phenyl group or an acyl group containing from 2 to 12 carbon atoms, preferably an acetyl or benzoyl group,
- $\text{R}_8$  represents a hydrogen atom, an alkyl group containing from 1 to 12 carbon atoms, a cycloalkyl group containing from 3 to 8 carbon atoms, an arylalkyl group containing from 6 to 12 carbon atoms, an aryl group containing from 6 to 12 carbon atoms or a heterocyclic group containing from 4 to 7 carbon atoms,
- $\text{R}_{10}$  represents a hydrogen atom or a linear or branched alkyl group containing from 1 to 4 carbon atoms.

Mention may be made more particularly of:

- methyl  $\alpha$ -acetamidocinnamate,
- methyl acetamidoacrylate,
- benzamidocinnamic acid,
- $\alpha$ -acetamidocinnamic acid.

A second preferred group of substrates consists of itaconic acid and derivatives thereof of formula:




in which:

- $R_{11}$  and  $R_{12}$ , which may be identical or different,  
 5 represent a hydrogen atom, a linear or branched alkyl group containing from 1 to 12 carbon atoms, a cycloalkyl group containing from 3 to 8 carbon atoms, an arylalkyl group containing from 6 to 12 carbon atoms, an aryl group containing from 6 to  
 10 12 carbon atoms or a heterocyclic group containing from 4 to 7 carbon atoms,
- $R_{10}$  and  $R'_{10}$ , which may be identical or different,  
 represent a hydrogen atom or a linear or branched alkyl group containing from 1 to 4 carbon atoms.

15 -

More particular examples that may especially be mentioned include itaconic acid and dimethyl itaconate.

A third preferred group of substrates is defined by  
 20 formula ( $A_3$ ):



in which:

- $R''_{10}$  represents a hydrogen atom or a linear or  
 25 branched alkyl group containing from 1 to 4 carbon

atoms,


- $R_{13}$  represents a phenyl or naphthyl group optionally bearing one or more substituents.

5 Specific examples that may be mentioned include the substrates leading via hydrogenation to 2-(3-benzoyl-phenyl)propionic acid (Ketoprofen<sup>®</sup>), 2-(4-isobutyl-phenyl)propionic acid (Ibuprofen<sup>®</sup>) and 2-(5-methoxy-naphthyl)propionic acid (Naproxen<sup>®</sup>).

10

As regards the hydrogenation of carbonyl bonds, the ruthenium complexes are more particularly suitable for the asymmetric catalysis of hydrogenation reactions of the C=O bonds of  $\beta$ -keto esters, of  $\alpha$ -keto esters or of  
15 ketones.

The appropriate substrates of ketone type more preferably correspond to formula (B):



20

in which:

- $R_{14}$  is different than  $R_{15}$ ,
- $R_{14}$  and  $R_{15}$  represent a hydrocarbon-based group  
25 containing from 1 to 30 carbon atoms optionally comprising one or more functional groups,
- $R_{14}$  and  $R_{15}$  may form a ring optionally comprising another hetero atom.

30 These compounds are described specifically in FR 96/08060 and EP 97930607.3.

One preferred group of ketone compounds corresponds to formula (B) in which  $R_{14}$  and  $R_{15}$  represent, independently of each other:

- 5       - an alkyl chain, preferably of  $C_1$  to  $C_{10}$ , optionally interrupted with one or more oxygen or sulfur atom(s) or carbonyl function(s) and optionally substituted with one or more halogen atoms or carboxyl groups,
- 10       - an alkenyl or alkynyl chain, preferably of  $C_2$  to  $C_{10}$ , optionally interrupted with one or more oxygen or sulfur atom(s) or carbonyl function(s) and optionally substituted with one or more halogen atom(s) or carboxyl group(s);
- 15       - an aryl group, preferably of  $C_6$  to  $C_{12}$ , optionally substituted with one or more halogen atom(s) or alkyl or alkenyl group(s);
- an arylalkyl group, preferably of  $C_7$  to  $C_{15}$ , optionally substituted with one or more halogen
- 20       atoms;
- an arylalkenyl group, preferably of  $C_8$  to  $C_{15}$ , optionally substituted with one or more halogen atoms; and
- \* indicates the optional presence in  $R_{15}$  of an
- 25       asymmetric center located in the position  $\alpha$  to the carbonyl function.

By way of representation of the substituents  $R_{15}$  containing an asymmetric center, mention may be made particularly of groups  $R_{15}$  in which the carbon atom bearing the asymmetric center is substituted with a

30       mono- or disubstituted amine function and with an ester function.

35       According to one particularly preferred embodiment of the invention, the substrate is a  $\beta$ -keto ester (such as

ethyl acetoacetate or methyl 3-oxovalerate), an  $\alpha$ -keto ester (such as methyl benzoylformate or methyl pyruvate), a ketone (such as acetophenone) or an  $\alpha,\beta$ -ethylenic carboxylic acid (such as itaconic acid) or an  
5 unsaturated amino acid or a derivative thereof (such as methyl 2-acetamidoacrylate).

The invention moreover relates to the use of a combination of a chiral diphosphine or of an optically  
10 active polymer according to the invention with a chiral or achiral diamine, for the selective reduction of ketones.


Advantageously, a chiral diamine is used in this  
15 combination.

The diamines that may be used for this purpose are the optically active diamines described in WO 97/20789 and the corresponding racemic diamines.

20 According to one particularly preferred embodiment of the invention, the diamine is 1,2-diamino-1,2-diphenylethane; 1,1-bis(p-methoxyphenyl)-2-methyl-1,2-diaminoethane; 1,1-bis(p-methoxyphenyl)-2-isobutyl-1,2-diaminoethane;  
25 aminoethane; or 1,1-bis(p-methoxyphenyl)-2-isopropyl-1,2-diaminoethane.

Examples of chiral diamines are more particularly those of formula:

30



in which  $G_4$  is alkyl, for example methyl, isobutyl or isopropyl.

5

Mention will be made more particularly of the achiral ethylenediamine and of achiral or chiral 1,2-diamino-1,2-diphenylethane, such as R,R-1,2-diamino-1,2-diphenylethane.

10

The ketones that may be reduced according to this process are those described above.

The conditions for performing the reduction are those  
15 generally described above.

The invention also relates to the use of the combination of an achiral diphosphine or of a racemic polymer, according to the invention, with a chiral diamine, for  
20 the selective reduction of ketones.

The chiral diamine that may be used is as described in WO 97/20789, the ketones and the operating conditions being as defined above.

25

The rhodium complexes prepared from the ligands of the invention are more especially suitable for the asymmetric catalysis of olefin isomerization reactions.

30 The use of a ligand of formula (Ia<sub>3</sub>) or polymers derived








therefrom such as polyurea, polyamide or polyimine intended for the asymmetric catalysis of hydrogenation reactions, forms a preferred subject of the invention.

- 5 The examples that follow more specifically illustrate the invention.

The meaning of the abbreviations used is given below.

10

Ligand name	Formula
BINAPO	
5,5'-dibromoBINAPO	
5,5'-dicyanoBINAPO	
5,5'-dicyanoBINAP	



The examples that follow illustrate the invention more specifically.

5 Example 1:

Preparation of 5,5'-dibromoBINAPO:

*Preparation of BINAPO:*

(S)- or (R)-BINAP (2,2'-bis(diphenylphosphino)-1,1'-  
10 binaphthyl) (3 g, 4.81 mmol, 1 eq.) dissolved in 100 mL  
of  $\text{CH}_2\text{Cl}_2$  is placed in a 250 mL round-bottomed flask.

The mixture is cooled to  $0^\circ\text{C}$  and 10 mL of 35% by weight  
aqueous hydrogen peroxide solution are added.

15

The mixture is stirred while being allowed to return to  
room temperature, for four hours.

100 mL of water are then added.

20

The organic phase is separated out and the aqueous  
phase is extracted with  $\text{CH}_2\text{Cl}_2$ .

The combined organic phases are washed with saturated  
25 sodium bisulfite.

The solution is checked for the absence of peroxide,  
and is then dried over sodium sulfate and evaporated.

A white solid is obtained ( $m = 3.14$  g,  $4.8$  mmol, i.e. quantitative yield).

- 5 The characterization of the diphosphine in dioxide form (BINAPO) is as follows:
- $^1\text{H}$  NMR (300 MHz,  $\text{CDCl}_3$ ): 6.80 (d, 4H,  $J = 3.7$ ), 7.2-7.3 (m, 8H), 7.3-7.5 (m, 12H), 7.6-7.7 (m, 4H), 7.8-7.9 (m, 4H)
  - 10 -  $^{31}\text{P}$  NMR (81 MHz,  $\text{CDCl}_3$ ): 28.67
  - melting point: 256-258°C

*Preparation of 5,5-dibromoBINAPO:*

- 15 Iron filings (622 mg, 11.1 mmol, 1.5 eq.), 65 mL of  $\text{CCl}_4$  and dibromine (7.6 mL, 148 mmol, 20 eq.) are placed in a dry 100 mL round-bottomed flask equipped with a condenser and a  $\text{CaCl}_2$  guard tube.
- 20 The mixture is heated to 70°C, followed by portionwise addition of BINAPO (4.8 g, 7.4 mmol, 1 eq.) dissolved in 45 mL of  $\text{CCl}_4$ .

The mixture is stirred at 70°C for 3 hours.

- 25 After checking by thin layer chromatography that the reaction is complete, the mixture is transferred into a separating funnel and washed with water, with sodium bisulfite, with sodium bicarbonate and then with brine.

- 30 The resulting solution is dried over sodium sulfate and then filtered through silica and eluted with ethyl acetate.

- 35 The solution thus obtained is evaporated under reduced pressure (about 8 mmHg).

A white solid is obtained ( $m = 4.85$  g, 6 mmol, i.e. a yield of 80.7%).

5 The characterization of the diphosphine (PO) in dibromo form is as follows:

- $^1\text{H}$  NMR (200 MHz,  $\text{CDCl}_3$ ): 6.62 (t, 2H,  $J = 15.0$ ), 6.72 (d, 2H,  $J = 9.0$ ), 7.2-7.5 (m, 22H), 7.55 (dd, 2H,  $J = 3.0$ ; 21.0), 7.6-7.8 (m, 4H), 8.3 (dd, 2H,  $J = 1.7$ ; 9.0)
- 10 -  $^{31}\text{P}$  NMR (81 MHz,  $\text{CDCl}_3$ ): 29.20
- melting point  $> 300^\circ\text{C}$

Example 2:

Preparation of 5,5'-dicyanoBINAPO:

15

5,5'-DibromoBINAPO (4.7 g, 5.8 mmol, 1 eq.) and copper cyanide (1.04 g, 16.24 mmol, 2.8 eq.) are placed in a 250 mL round-bottomed flask under an inert atmosphere, equipped with a condenser.

20

The mixture is dissolved in 70 mL of DMF and is refluxed overnight.

25 The mixture is cooled and then treated with a solution of ethylenediamine (25 mL) and water (25 mL).

The mixture is stirred for 2 minutes, and 100 mL of water and 200 mL of toluene are then added.

30 The mixture is stirred for 5 minutes and the aqueous phase is then extracted once with toluene.

The combined organic phases are successively washed once with water, four times with HCl, once with brine  
35 and then once with sodium bicarbonate.

The product is then dried over sodium sulfate, and then evaporated under reduced pressure (about 8 mmHg) (m = 3.71 g, 5.5 mmol, i.e. a yield of 90.8%).

- 5 The product is purified on a column of silica gel, eluting with ethyl acetate/cyclohexane (4/6).

2.52 g (3.75 mmol, i.e. a yield of 61.7%) of pure white product are obtained.

10

The characterization of the diphosphine (PO) in dicyano form is as follows:

- $^1\text{H}$  NMR (200 MHz,  $\text{CDCl}_3$ ): 6.85 (dd, 2H,  $J = 7.0$ ; 7.1), 6.97 (d, 2H,  $J = 9.0$ ), 7.2-7.5 (m, 24H), 7.6-7.7 (m, 15 6H), 7.8 (dd, 2H,  $J = 1.1$ ; 6.1), 8.33 (dd, 2H,  $J = 1.9$ ; 7.1)
- $^{31}\text{P}$  NMR (81 MHz,  $\text{CDCl}_3$ ): 29.1
- ESI $^+$  mass:  $\text{MH}^+ = 705$
- melting point  $> 300^\circ\text{C}$

20

Example 3:

Preparation of 5,5'-dicyanoBINAP:

5,5'-DicyanoBINAPO (420 mg, 0.6 mmol) is placed in a dry 25 mL round-bottomed flask under an inert atmosphere, equipped with a condenser.

Phenylsilane (8 mL, 64.8 mmol) is added and the suspension is degassed under reduced pressure (about 8 30 mmHg) and argon is introduced.

The mixture is heated to  $130^\circ\text{C}$  and trichlorosilane is added in three portions ( $3 \times 1$  mL) after 1 hour, 3 hours and then 15 hours; the mixture is then stirred 35 for a further 2 hours.

The resulting mixture is cooled and the product is evaporated to give a white solid.

This solid is washed with cyclohexane, filtered on a  
5 Millipore filter and then dried under reduced pressure (about 8 mmHg).

Pure (*S*) or (*R*) products are obtained in quantitative yields.

10

The characterization of the diphosphine in dicyano form is as follows:

- $^1\text{H}$  NMR (300 MHz,  $\text{CDCl}_3$ ): 6.63-6.81 (m, 4H), 7.04-7.30 (m, 20H), 7.42 (d, 2H,  $J = 7.14$ ), 7.56 (d, 2H,  $J =$   
15 8.85), 8.33 (d, 2H,  $J = 9.03$ )
- $^{31}\text{P}$  NMR (81 MHz,  $\text{CDCl}_3$ ): -13.99.

Example 4:

Preparation of 5,5'-diaminomethylBINAP:

20

5,5'-DicyanoBINAP (400 mg, 0.6 mmol) is placed in a 100 mL round-bottomed flask under an argon atmosphere.

The product is dissolved in a (1:1) mixture of 22.5 mL  
25 of THF and 22.5 mL of toluene.

$\text{LiAlH}_4$  (227.7 mg, 6 mmol) is then added portionwise.

The mixture is heated at 105°C for 2 hours.

30

The resulting mixture is cooled, and 0.5 mL of water and 0.5 mL of sodium hydroxide solution (15% by mass) are then added.

35 After stirring for three minutes, 1.5 g of Celite are added.

After five minutes, the mixture is then filtered and the residue is washed with dichloromethane.

- 5 The filtrate is evaporated and then dried under reduced pressure (about 8 mmHg) to give a yellow-white solid.

The product is obtained in quantitative yield.

- 10 The characterization of the diphosphine in diaminomethyl form is as follows:

- $^1\text{H}$  NMR (200 MHz,  $\text{CDCl}_3$ ): 1.62 (s, 4H), 4.37 (s, 4H), 6.8-7.0 (m, 4H), 7.1-7.3 (m, 20H), 7.36 (d, 2H,  $J = 6.58$ ), 7.51 (d, 2H,  $J = 8.82$ ), 8.15 (d, 2H,  $J = 8.82$ )
- 15 -  $^{31}\text{P}$  NMR (81 MHz,  $\text{CDCl}_3$ ): -15.50
- $^{13}\text{C}$  NMR (50 MHz,  $\text{CDCl}_3$ ): 44.30; 122.92; 125.61; 125.93; 127.32; 128.12; 128.30; 128.44; 128.71; 129.02; 129.31; 130.04; 132.57; 132.88; 133.18; 133.81; 135.23; 139.42
- 20 -  $\alpha_{\text{D}}$  ( $c = 1$ , DMF): -100.3 for (S)
- $\alpha_{\text{D}}$  ( $c = 1$ , DMF): +101.4 for (R)

#### Example 5

##### 1 - Hydrogenation test:

25

The procedure followed is given below.

- 5,5'-DiamBINAP (17.5 mg, 0.0235 mmol, 1 eq.) dissolved in 1 mL of dichloromethane is placed in a 5 mL vial
- 30 under an inert atmosphere, bis(2-methylallyl) cycloocta-1,5-dieneruthenium (II) complex (7.5 mg, 0.0235 mmol, 1 eq.) is added and the mixture is stirred for 30 minutes.

- 35 The solvent is then evaporated off.

1 ml of methanol (or ethanol) is added and the substrate is then placed in an autoclave under a hydrogen pressure of 40 bar at 50°C and stirred for 15 hours.

5

The autoclave is then cooled and depressurized.

The solution is filtered through Celite and then analyzed by gas chromatography.

10

## 2 - Hydrogenation of ethyl or methyl acetoacetate

This is performed as described above with a substrate/catalyst ratio of 1000.

15

The results obtained are as follows:

Substrate	Conversion (%)	e.e.* (%)
Ethyl acetoacetate	100	> 99
Methyl acetoacetate	100	> 99

$$*ee = \frac{\% (R) - \% (S)}{\% (R) + \% (S)}$$

20

These results are confirmed whether 5,5'-diamBINAP is used in (S) or (R) form.

The configuration of the corresponding alcohol obtained depends on the chirality of the ligand used.

25

### Examples 6 and 7

#### Preparation of (R)-5,5'-perfluorohexylBINAPO and (R)-5,5'-perfluorooctylBINAPO

30

5,5'-DibromoBINAPO (2.46 mmol, 1 eq.), copper powder (14.76 mmol, 6 eq.) and the alkyl iodoperfluoride



(7.38 mmol, 3 eq.), i.e. hexyl in example 6 and octyl in example 7, are placed in a 250 mL round-bottomed flask under an argon atmosphere.

- 5 The mixture is dissolved in 40 mL of DMSO and heated at 80°C for 3 days.

The mixture is then cooled and 20 mL of water and 40 mL of dichloromethane are then added.

10

The resulting mixture is filtered and the organic phase is recovered.

- 15 This phase is washed with 10 mL of water, 20 mL of hydrochloric acid and 15 mL of sodium bicarbonate.

The solution is dried and evaporated to give 2.33 mmol of a cream-white powder (94.7%).

- 20 The characterization of the diphosphine (R)-5,5'-perfluorohexylBINAPO is as follows:

- $^1\text{H}$  NMR (300 MHz,  $\text{CDCl}_3$ ): 6.73-6.91 (m, 4H), 7.17-7.41 (m, 18H), 7.51 (dd, 2H,  $J = 9.4, 11.7$ ), 7.63-7.72 (m, 4H), 8.27 (d, 2H,  $J = 8.3$ )
- 25 -  $^{13}\text{C}$  NMR (75 MHz,  $\text{CDCl}_3$ ): 116.3, 120.2, 124.5, 124.8, 125.3, 126.5, 128.4, 128.5, 128.6, 128.7, 128.9, 129.4, 129.7, 130.1, 130.3, 130.4, 131.1, 131.4, 131.6, 132.1, 132.2, 132.3, 132.7, 132.8, 133.1
- $^{31}\text{P}$  NMR (81 MHz,  $\text{CDCl}_3$ ): 28.33
- 30 -  $^{19}\text{F}$  NMR (282 MHz,  $\text{CDCl}_3$ ): -126.37 (s, 4F), -123.01 (s, 4F), -121.79 (s, 4F), -120.64 (s, 4F), -105.21 (s, 4F), -81.15 (s, 6H)
- $[\alpha_D]^{25}$ : +72.1 ( $c = 1$ , DMF)
- ESI $^+$ :  $\text{MH}^+ = 1291.24$
- 35 - melting point: > 300°C. Calcd C 52.11, H 2.34, F 38.27; found C 52.02, H 2.47, F 38.45

The characterization of the diphosphine (R)-5,5'-perfluorooctylBINAPO is as follows:

- $^1\text{H}$  NMR (300 MHz,  $\text{CDCl}_3$ ): 6.75-6.96 (m, 4H), 7.19-7.40 (m, 18H), 7.56 (dd, 2H,  $J = 9.4, 11.7$ ), 7.65-7.73 (m, 4H), 8.28 (d, 2H,  $J = 8.6$ )
- $^{13}\text{C}$  NMR (75 MHz,  $\text{CDCl}_3$ ): 124.5, 124.9, 125.2, 126.7, 128.4, 128.5, 128.6, 128.7, 128.8, 129.3, 129.7, 130.1, 130.2, 130.4, 130.9, 131.5, 131.6, 132.0, 132.2, 132.3, 132.7, 132.8, 130.9
- $^{31}\text{P}$  NMR (81 MHz,  $\text{CDCl}_3$ ): 28.58
- $^{19}\text{F}$  NMR (282 MHz,  $\text{CDCl}_3$ ): -126.54 (s, 4F), -123.09 (s, 4F), -122.26 (s, 8F), -121.64 (s, 4F), -120.19 (s, 4F), -104.35 (s, 4F), -81.18 (s, 6F)
- $[\alpha_D]^{25}$ : +73.4 ( $c = 1$ , DMF)
- ESI $^+$ :  $\text{MH}^+ = 1491.54$
- melting point:  $> 300^\circ\text{C}$ . Calcd C 48.34, H 2.03, F 43.33; found C 48.91, H 1.88, F 43.67

## 20 Examples 8 and 9

### Preparation of (R)-5,5'-perfluorohexylBINAP and (R)-5,5'-perfluorooctylBINAP

(R)-5,5'-PerfluoroalkylBINAPO (0.6 mmol, 1 eq.) is placed in a 25 mL round-bottomed flask under an inert atmosphere.

Degassed phenylsilane (8 mL) is added. The mixture is heated to  $130^\circ\text{C}$  and trichlorosilane is added in three portions ( $3 \times 1$  mL) after 1, 3 and 15 hours.

After the last addition, the solution is stirred for a further 2 hours and then cooled and evaporated until a white solid is obtained.

35

This residue is washed with cyclohexane (5 mL),

filtered through a Millipore filter and the remaining solvent is then evaporated off to give a white crystalline solid in a yield of 95%.

- 5 The characterization of the diphosphine (R)-5,5'-perfluorohexylBINAP is as follows:
- $^1\text{H}$  NMR (200 MHz,  $\text{CDCl}_3$ ): 6.78-6.98 (m, 4H), 7.13-7.47 (m, 18H), 7.50-7.61 (m, 2H), 7.65-7.78 (m, 4H), 8.29 (d, 2H,  $J = 7.3$ )
  - 10 -  $^{13}\text{C}$  NMR (75 MHz,  $\text{CDCl}_3$ ): 123.1, 123.3, 124.5, 124.6, 124.8, 125.6, 126.5, 127.1, 127.3, 128.1, 128.2, 128.4, 128.5, 128.7, 130.0, 131.4, 131.8, 132.1, 132.2, 132.4, 132.8, 132.9, 133.2, 133.4, 133.6, 134.4, 134.5, 135.0, 135.4, 135.7, 138.1, 138.4, 143.9, 144.2, 144.7, 145.1
  - 15 -  $^{31}\text{P}$  NMR (81 MHz,  $\text{CDCl}_3$ ): -13.27
  - $^{19}\text{F}$  NMR (282 MHz,  $\text{CDCl}_3$ ): -126.37 (s, 4F), -123.01 (s, 4F), -121.79 (s, 4F), -120.64 (s, 4F), -105.21 (s, 4F), -81.15 (s, 6H)
  - $[\alpha_D]^{25}$ : +35.7 ( $c = 1$ , DCM)
  - 20 - melting point:  $> 300^\circ\text{C}$
  - HRLSIMS:  $\text{MH}^+$  calc. 1259, 1408, found 1259, 1398

The characterization of the diphosphine (R)-5,5'-perfluorooctylBINAPO is as follows:

- 25 -  $^1\text{H}$  NMR (300 MHz,  $\text{CDCl}_3$ ): 6.77-6.96 (m, 4H), 7.02-7.10 (m, 4H), 7.26-7.42 (m, 14H), 7.55-7.61 (m, 6H), 8.29 (d, 2H,  $J = 8.9$ )
- $^{13}\text{C}$  NMR (75 MHz,  $\text{CDCl}_3$ ): 124.4, 125.4, 126.6, 128.3, 128.4, 128.4, 128.5, 128.6, 128.6, 128.7, 128.8, 128.8, 128.9, 129.3, 129.5, 130.8, 132.0, 132.2, 133.0, 133.2, 133.3, 133.4, 133.6, 133.7, 134.4, 134.5, 134.9, 135.2, 135.4, 135.8, 137.0, 137.4, 137.5, 138.2, 144.0, 144.3, 144.6
- 30 -  $^{31}\text{P}$  NMR (81 MHz,  $\text{CDCl}_3$ ): -13.18
- 35 -  $^{19}\text{F}$  NMR (282 MHz,  $\text{CDCl}_3$ ): -126.59 (s, 4F), -123.17 (s, 4F), -122.29 (s, 8F), -121.72 (s, 4F), -120.35 (s, 4F),


- 104.46 (s, 4F), -81.27 (s, 6H)
- $[\alpha_D]^{25}$ : +35.5 (c = 1, DCM)
- melting point: > 300°C
- HRLSIMS:  $MH^+$  calc. 1459, 1280, found 1459, 1271

5

Examples 10 and 11Hydrogenation test

In order to evaluate the activities of these novel  
 10 ligands and the influence of the perfluoro chains, the  
 corresponding metal complexes were prepared by reaction  
 with  $[RuCl_2(benzene)]_2$  in accordance with the general  
 procedure described by Noyori et al. [Kitamura, M.;  
 Tokunaga, M.; Ohkuma, T.; Noyori, R. *Tetrahedron Lett.*  
 15 1991, 32, 4163].

The complexes were tested for the catalytic  
 hydrogenation of several  $\beta$ -keto esters.



20

The results are given in the following table:

Ex. ref.	Ligand	Complex	R	Substrate/ catalyst in mol	Conversion (%)	e.e. (%)
10	ex 8	$[RuCl_2(benzene)]_2$	Me	1000	100	99
11	ex 8	$[RuCl_2(benzene)]_2$	Et	2000	100	99

Example 12:

25 Preparation of a polyurea starting with (S)-5,5'-  
diaminomethylBINAP (diamBINAP)

The starting diamBINAP (200 mg, 0.29 mmol) prepared according to the procedure described in examples 1 to 4 is placed in a 10 mL round-bottomed flask.

5 This material is dissolved in 2 mL of degassed anhydrous dichloromethane.

2,6-Diisocyanatotoluene (51 mg, 0.29 mmol) is added under argon.

10

The solution is stirred for 12 hours and 2 mL of degassed isopropanol are then added.

The solid is filtered off and then washed with  
15 isopropanol.

240 mg of polymer (yellow powder) are obtained, i.e. a yield of 96%.

20 The characterization of the 5,5'-polyNAP obtained is as follows:

- $[\alpha_D] = -103^\circ$  ( $c = 0.356$ , DMF)
- $^1\text{H}$  NMR (DMSO, 200 MHz): 1.03 (d,  $\text{CH}_3$ ); 1.22 (d,  $\text{CH}_3$ ); 2.03 (m,  $\text{CH}_3$  tolyl); 3.34 (s,  $\text{CH}_2$ ); 6.67 (d, CH); 6.70-  
25 7.50 (m); 7.73 (s, CH); 8.25 (d, CH).
- $^{31}\text{P}$  NMR (DMSO, 81 MHz): -16.53.

#### Example 13

Preparation of a ruthenium catalyst starting with the  
30 polymer prepared in example 12

The polymer and the metallic precatalyst bis(2-methylallyl)cycloocta-1,5-dieneruthenium are weighed out, in a 1:1 polymer/metal molar ratio, in a dry 5 mL  
35 glass conical reactor maintained under an inert atmosphere and equipped with a stirrer.

2 mL of degassed anhydrous acetone are added and the suspension is stirred for 30 minutes.

- 5 A 48% by weight solution of hydrobromic acid is then added in an Ru/Br ratio of 1/2.3.

The solution then turns dark orange.

- 10 The solution is stirred for 1 hour and then evaporated.

The catalyst is then obtained in the form of a brown solid.

- 15 Example 14

Hydrogenation of ethyl acetoacetate using the catalyst prepared in example 13

- 20 Degassed anhydrous ethanol is added to the reactor in which the catalyst has just been prepared.

The substrate is then added (in a defined catalyst/substrate ratio).

- 25 The reactor is placed in an autoclave under a hydrogen pressure of 40 bar and at 50°C.

Stirring is maintained overnight.

- 30 The reactor is recovered and then centrifuged.

The supernatant solution is recovered and then analyzed by gas chromatography.

- 35 The determination of the enantiomeric excess is performed by chiral gas chromatography on a Lipodex A

25 m x 0.25 mm column.

The results obtained are given in the following table:

Catalyst (5,5'-polyNAP)	Substrate/catalyst in mol	Conversion (%)	e.e. (%)
5,5'	1000	100	83
5,5'	500	100	85
5,5' (recycled)	500	100	90

5

The hydrogenation of ethyl acetoacetate leads to ethyl 3-hydroxybutyrate.

#### Example 14

10 Hydrogenation of 2-methylacetamidoacrylate using the catalyst prepared in example 13

Degassed anhydrous ethanol is added to the reactor in which the catalyst has just been prepared.

15

The substrate is then added (in a defined catalyst/substrate ratio).

20 The reactor is placed in an autoclave under a hydrogen pressure of 40 bar and at 50°C.

Stirring is maintained for 6 hours.

The reactor is recovered and then centrifuged.

25

The supernatant solution is recovered and then analyzed by gas chromatography.

30 The determination of the enantiomeric excess is performed by chiral gas chromatography on a  $\beta$ dex A 60 m

× 0.25 mm column.

The results obtained are given in the following table:

Catalyst (5,5'-polyNAP)	Substrate/catalyst in mol	Conversion (%)	e.e. (%)
5,5'	300	100	70